

PRODUKTDATENBLATT

SikaMembran® Strong

EPDM-Folienmembran für die äußere Abdichtung von Fassaden mit hoher mechanischer Festigkeit

TYPISCHE PRODUKTEIGENSCHAFTEN

Chemische Basis	Synthesekautschuk auf Basis EPDM
Farbe	Schwarz (mit Folienbezeichnung bedruckt)
Flächengewicht	1,6 kg/m ²
Schichtdicke	1,2 mm
Äquivalente Luftschichtdicke	sd value 79 m
Elongation at break (ISO 37)	400 %
Verarbeitungstemperatur	5 – 40 °C
Tensile strength (ISO 37)	7.5 MPa
Weiterreißwiderstand (CQP 045-1 / ISO 34)	8 N/mm
Ozonbeständigkeit	200 pphm, 40 °C, 20 % Elongation, 168 h
Einsatztemperatur	-40 – 90 °C
Haltbarkeit	18 months ^A

CQP = Corporate Quality Procedure

^{A)} stored in dry conditions between 5 and 30 °C and protected from direct sunlight

BESCHREIBUNG

SikaMembran® Strong is robust EPDM sheet membrane with a very high mechanical strength and an s_d value of 79 m. The SikaMembran® system is a high-performance vapor control system comprising of various EPDM sheet membranes providing vapor control layers and waterproof barriers for curtain walls. They are suitable for most climatic conditions in combination with the appropriate adhesive.

PRODUKTVORTEILE

- Highly flexible waterproofing and vapor control system
- Fast and secure application
- Provided with CE-mark according to EN 13984: 2011
- Meet fire retardant requirements of EN 13501-1 Class E under free suspension
- No additional mechanical fixing necessary
- Membrane pre-treatment free
- Suitable for uneven substrates (blowholes in concrete), leveling of substrate by adhesive
- Suited to site conditions
- Durable bond and barrier/seal
- Ozone- and UV-resistant

ANWENDUNGSBEREICH

The flexible SikaMembran® sheets, installed between structure and incorporated units (e.g. facade elements, windows, etc.) using SikaBond® TF plus N adhesive, provide a secure and durable vapor barrier and waterproof seal at junctions between building elements mainly in curtain wall facades but also in ventilated facades and window installations. This product is suitable for experienced professional users only. Test with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

DESIGN CONSIDERATION

In order to prevent thermal bridging or internal condensation ensure adequate provision of insulation (mineral wool or similar) within the joint prior to sealing.

Always follow local construction and fire regulations.

Design details need to be determined by the responsible engineer and building physicist.

VERARBEITUNGSHINWEISE

Oberflächenvorbehandlung

Prior the bonding process ensure that substrates are sound, clean, dry, free from dust, grease, oil and loose particles.

Verarbeitung

Apply SikaBond® TF plus N adhesive to the corresponding structure or components (nozzle diameter approx. 8 mm).

By using a clean spatula, spread the adhesive bead to approx. 4 – 5 cm width and 1 mm thickness.

Install the SikaMembran® Strong sheet tension-free and in a way that movement of the connected building parts can be accommodated without damaging the membrane. Press the membrane sheet on the adhesive by a plastic roller. The membrane must be fully bonded over a width of 4 cm. Where overlaps are required ensure at least an overlap of 5 cm.

The membrane might be re-adjusted during a period of 30 minutes after installation.

Anwendungsgrenzen

SikaMembran® Strong is not resistant to mineral oils, petroleum, benzene, fuel and toluene etc.

The bond line of the membrane must not be in permanent contact with water.

GEBINDE

Length [m / roll]	25
Width of rolls [mm]	100, 150, 200, 250, 300, 350, 400, 450, 500, 600, 700, 1200, 1400

WEITERE INFORMATIONEN

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- General Guideline
SikaMembran® System

HINWEIS MESSWERTE

Alle in diesem Datenblatt genannten technischen Werte basieren auf Laborversuchen. Aufgrund von uns nicht beeinflussbarer Umstände können aktuell gemessene Werte variieren.

RECHTLICHE HINWEISE

Die vorstehenden Angaben, insbesondere die Vorschläge für Verarbeitung und Verwendung unserer Produkte, basieren auf unseren derzeitigen Kenntnissen und Erfahrungen im Normalfall. Sie befreien den Anwender wegen der Fülle möglicher Einflüsse bei der Lagerung, Verarbeitung und Anwendung unseres Produktes nicht von eigenen Prüfungen und Versuchen vor der Anwendung. Wegen der unterschiedlichen Materialien, Untergründe und abweichenden Arbeitsbedingungen kann eine Gewährleistung eines Arbeitsergebnisses oder eine Haftung, aus welchen Rechtsverhältnissen und -titeln auch immer, weder aus diesen Hinweisen noch aus einer schriftlichen Beratung begründet werden, es sei denn, dass uns insoweit Vorsatz oder grobe Fahrlässigkeit zur Last fällt. Sonstige Äußerungen unserer Mitarbeiter über die Brauchbarkeit von Waren, ihren Verwendungszweck oder ihre Verarbeitung sind für uns solange nicht rechtsverbindlich, solange sie nicht in Briefform mit eigenhändiger Unterschrift des Mitarbeiters ausdrücklich bestätigt worden sind. Unsere Mitarbeiter sind darüber hinaus nicht bevollmächtigt, rechtsverbindliche Äußerungen zur Brauchbarkeit, zum Verwendungszweck oder zur Verarbeitung unserer Waren abzugeben. In allen gegen uns geltend gemachten Haftungsfällen hat der Anwender nachzuweisen, dass er uns schriftlich alle Informationen, die zur sachgemäßen und erfolversprechenden Beurteilung durch uns erforderlich sind, rechtzeitig und vollständig übermittelt hat. Die Anwendung des Produkts in Anwendungsgebieten, die nicht in der Gebrauchsanweisung oder einer sonstigen Anleitung beschrieben sind, ist von uns nicht geprüft. Dies gilt insbesondere für Anwendungen, die zwar von einer Zulassung oder Genehmigung durch die Zulassungsbehörde erfasst sind, aber von uns nicht explizit empfohlen werden. Wir schließen deshalb jegliche Haftung für eventuelle Schäden aus einer solchen Anwendung aus. Alle hierin gemachten Angaben und Informationen können sich ohne Vorankündigung ändern. Wir empfehlen daher, vor jeder Anwendung die Aktualität der Produktinformation auf aut.sika.com/de/download-center-industrie/produktdatenblaetter.html (Downloadcenter) zu prüfen. Im Übrigen gelten – auch gegenüber Dritten – unsere aktuellen Verkaufs- und Lieferbedingungen, abrufbar unter www.sika.at/agb.