



PRODUCT DATA SHEET

Sikaflex®-545

High initial grab STP assembly adhesive

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base	Silane Terminated Polymer
Colour (CQP001-1)	White
Cure mechanism	Moisture-curing
Density (uncured)	1.4 kg/L
Non-sag properties (CQP061-1)	Excellent
Application temperature	ambient 5 °C - 40 °C
Skin time (CQP019-1)	15 minutes ^A
Open time (CQP526-1)	10 minutes ^A
Curing speed (CQP049-1)	(see diagram)
Shore A hardness (CQP023-1 / ISO 48-4)	45
Tensile strength (CQP036-1 / ISO 527)	2.5 MPa
Elongation at break (CQP036-1 / ISO 527)	400 %
Tear propagation resistance (CQP045-1 / ISO 34)	7 N/mm
Tensile lap-shear strength (CQP046-1 / ISO 4587)	1.5 MPa
Service Temperature (CQP509-1 / CQP513-1)	-50 °C - 90 °C
Shelf life	Cartridge / Unipack 15 months ^B Pail / Drum 9 months ^B

CQP = Corporate Quality Procedure

^{A)} 23 °C / 50 % r.h.

^{B)} storage below 25 °C

DESCRIPTION

Sikaflex®-545 is a low emission 1-component Silane Terminated Polymer (STP) assembly adhesive. It has a unique high initial grab with high load capacity and excellent workability. It bonds well to a wide range of substrates with minimal pre-treatment.

PRODUCT BENEFITS

- Powerful initial grab
- Very low emission
- Bonds well to a wide variety of substrates without the need for special pre-treatments
- Excellent workability
- Free of isocyanate, solvent and phthalate
- Meets highest EHS standards
- EC1 certificate
- Meets the requirements of ASTM C557 - bonding drywall

AREAS OF APPLICATION

Sikaflex®-545 is especially designed for applications which require a very high initial grab and a broad adhesion range. Suitable substrate materials include timber, glass, metals, metal primers and paint coatings (2-part systems), ceramic materials and plastics. Seek manufacturer's advice and perform tests on original substrates before using Sikaflex®-545 on materials prone to stress cracking. Sikaflex®-545 is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

PRODUCT DATA SHEET

Sikaflex®-545

Version 06.01 (04 - 2023), en_CA

012201215450001000

CURE MECHANISM

Sikaflex®-545 cures by reaction with atmospheric moisture. At low temperatures the moisture content of the air is generally lower and the curing reaction is somewhat slower (see diagram 1).




Diagram 1: Curing speed Sikaflex®-545

CHEMICAL RESISTANCE

Sikaflex®-545 is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

METHOD OF APPLICATION

Surface Preparation

Surfaces must be clean, dry and free from grease, oil and dust. Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond. Suggestions for surface preparation may be found on the current edition of the appropriate Sika Pre-treatment Chart.

Consider that these suggestions are based on experience and must be in any case verified by tests on original substrates.

Application

Apply the adhesive with a suitable caulking gun. Take care to avoid air entrapment in the joint. Sikaflex®-545 can be processed between 5 °C and 40 °C but changes in reactivity and application properties have to be considered. The optimum temperature for substrate and sealant is between 15 °C and 25 °C.

Consider that the viscosity will increase at low temperature. For easy application, condition the adhesive at ambient temperature prior to use.

To ensure a uniform thickness of the bondline it is recommended to apply the adhesive in form of a triangular bead (see figure 1).




Figure 1: Recommended bead configuration

Sikaflex®-545 can be processed with manual, pneumatic or electric driven piston guns as well as pump equipment. The open time is significantly shorter in hot and humid climate. The parts must always be installed within the open time. Never join bonding parts if the adhesive has built a skin.

Tooling and finishing

Tooling and finishing must be carried out within the skin time of the adhesive. It is recommended using Sika® Tooling Agent N. Other finishing agents must be tested for suitability and compatibility prior the use.

Removal

Uncured Sikaflex®-545 can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H cleaning towels or a suitable industrial hand cleaner and water. Do not use solvents on skin.

Overpainting

Sikaflex®-545 can be best painted within the skin formation time. If painting process takes place after the sealant has built a skin, adhesion could be improved by treating the joint surface with Sika® Aktivator-100 or Sika® Aktivator-205 prior to paint process. If the paint requires a baking process (> 80 °C), best performance is achieved by allowing the sealant to fully cure first. All paints have to be tested by carrying preliminary trials under manufacturing conditions. The elasticity of paints is usually lower than that of sealants. This could lead to cracking of the paint in the joint area.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific application is available on request from Sika Canada.

Copies of the following publications are available on request:

- Safety Data Sheets
- Sika® Pre-treatment Chart
 - For Silane Terminated Polymers (STP)
- General Guideline
 - Bonding and Sealing with 1-component Sikaflex®

PACKAGING INFORMATION

Cartridge	300 mL
Unipack	600 mL
Drum	195 L

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

DISCLAIMER

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: www.sika.ca

PRODUCT DATA SHEET

Sikaflex®-545
Version 06.01 (04 - 2023), en_CA
012201215450001000

Sika Canada Inc.
Head Office
601, avenue Delmar
Pointe-Claire, Quebec
H9R 4A9
1-800-933-SIKA
www.sika.ca

