

## PRODUCT DATA SHEET

# SikaBlock® M980

Polyurethane tooling board

## TYPICAL PRODUCT DATA

Chemical base	Polyurethane
Color	Blue
Density	1.35 kg/l
Shore D hardness (CQP023-1 / ISO 868)	86
Compressive strength (CQP028-5 / ISO 604)	120 MPa
Flexural strength (CQP027-2 / ISO 178)	145 MPa
Flexural modulus (CQP027-2 / ISO 178)	4000 MPa
Impact resistance (CQP038-2 / ISO 179)	35 kJ/m <sup>2</sup>
Heat deflection temperature (CQP030-1 / ISO 75B)	85 °C
Linear coefficient of thermal expansion (CQP053-1 / ISO 11359)	60 x 10 <sup>-6</sup> 1/K

CQP = Corporate Quality Procedure

## DESCRIPTION

SikaBlock® M980 is a slightly filled blue polyurethane tooling board with high abrasion resistance for foundry patterns, match plates and core boxes.

## PRODUCT BENEFITS

- Very low coefficient of thermal expansion
- Easy to machine
- Very high abrasion resistance
- Very high compressive and flexural strength as well as edge stability
- Good swelling resistance

## AREAS OF APPLICATION

SikaBlock® M980 is well suited for foundry patterns, match plates and core boxes for cold box process.

It is also designed for wide range of molds, tools and gauges where high dimensional stability and good mechanical properties are required.

This product is suitable for experienced professional users only. The boards must be tested for the specific application in each case, e.g. type of sand molding process, binder, amine catalyst, etc.

## METHOD OF APPLICATION

### Product preparation

Before SikaBlock® M980 boards can be processed (machined) they must be conditioned to 18 °C – 25 °C.

If the boards need to be bonded, make sure that the surfaces are clean, dry and free of grease or oil. For cleaning Sika® Cleaner G+M or another suitable cleaner or solvent can be used.

For bonding SikaBlock® M980 boards together use SikaBiresin® B180. Further details on the adhesives can be found in the respective Product Data Sheet.

### Application

SikaBlock® M980 can be easily machined by milling, drilling, sawing or modified manually. It is recommended to use high performance tools to machine these boards.

For milling parameters check information from cutting tool manufacturers or get the General Guideline "Milling parameters for SikaBlock®" for more general information.

### STORAGE CONDITIONS

The board needs to be stored flat over the entire surface in dry conditions.

Many models and tools are made of bonded boards, either with identical or other materials. Storage at low and elevated temperature can lead to high stresses due to the different expansion coefficients. To prevent this, it is necessary to store the models and tools at a temperature range between 15 °C and 30 °C.

## FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Voluntary Safety Information Sheet
- General Guideline
- Milling parameters for SikaBlock®

## PACKAGING INFORMATION

Dimensions [mm]	Pcs./ pallet
1000 x 495 x 30	30
1000 x 495 x 50	36
1000 x 495 x 75	24
1000 x 495 x 100	18

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## HEALTH AND SAFETY INFORMATION

This product contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A Safety Data Sheet is therefore not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the Voluntary Safety Information Sheet.

## DISCLAIMER

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

## PRODUCT DATA SHEET

SikaBlock® M980  
Version 04.01 (10 - 2025), en\_DE  
012121039800001000

Sika Deutschland CH AG & Co KG  
Industry  
Stuttgarter Straße 139  
72574 Bad Urach  
Tel. +49 7125 940-7692  
verkauf.industry@de.sika.com  
www.sika.de

