

PRODUCT DATA SHEET

Sika MonoTop®-910 N

Polymer-modified corrosion protection and bonding primer for the Sika MonoTop PCC system

DESCRIPTION

Sika MonoTop®-910 N is a cementitious, polymer modified one-component coating material containing silica fume used as bonding primer and reinforcement corrosion protection.

USES

- Suitable for control of anodic areas (Principle 11, method 11.1 of EN 1504-9)
- Suitable as a bonding primer as part of a concrete repair system
- Suitable as reinforcement corrosion protection as part of a concrete repair system

PRODUCT INFORMATION

Packaging	25 kg bag
Appearance / Colour	Grey powder
Shelf life	12 months
Storage conditions	Store properly in undamaged original sealed packaging, in dry cool conditions between +5 °C and +35.
Density	Fresh mortar density ~2.0 kg/l
Soluble chloride ion content	≤ 0.01 % (EN 1015-17)

SYSTEM INFORMATION

System structure	Sika MonoTop®-PCC-System: <ul style="list-style-type: none"> ▪ Sika MonoTop®-910 N ▪ Sika MonoTop®-412 DE ▪ Sika MonoTop®-723 DE / Icoment®-520
------------------	--

CHARACTERISTICS / ADVANTAGES

- CE certified to EN 1504-7
- Can be applied with a brush or by wet spray technique
- Easy to use just add water
- Adhesion to concrete and steel
- Good resistance to water and chloride penetration

APPROVALS / CERTIFICATES

- The Sika MonoTop-PCC system is listed in the compilation of certified substances and substance systems according to ZTV-ING, Part 3, Section 4.
- Meets the requirements of EN 1504-7

APPLICATION INFORMATION

Mixing ratio	For brush application ~5.25 litre water (21%) per 25 kg bag For spraying application ~5.0 litre water (20%) per 25 kg bag			
Consumption	As Bonding Primer - This depends on the substrate roughness and thickness of layer applied. As a guide, ~1.5 – 2.0 kg of powder per m ² per mm thick. As Reinforcement Corrosion Protection - As a guide, ~2.0 kg of powder per m ² per 1mm layer thickness (2 application coats)			
Yield	25 kg of powder yields approximately 14.3 litres			
Layer thickness	As bonding primer - sufficient to coat the concrete surface in a thin layer filling unevenness, pores and pits As reinforcement corrosion protection - 2 mm minimum thickness			
Ambient air temperature	+5°C minimum; +30°C maximum			
Substrate temperature	+5°C minimum; +30°C maximum			
Pot Life	+5 °C	ca. 2 hours		
	+20 °C	ca. 1 hour		
	+35 °C	ca. 45 mins		
Waiting time to overcoating		+5 °C	+20 °C	+35 °C
	Bonding primer / Repair mortar	wet-to-wet	wet-to-wet	wet-to-wet
	after 1. applica- tion coat	~8 hours	~4 - 5 hours	~3-4 hours
	2. application coat / Bonding primer	~24 hours	~12 hours	~8 hours

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Refer to the Method Statement for Concrete Repair using Sika MonoTop® system for more information or EN 1504-10
- Avoid application in direct sun and/or strong wind and/or rain
- Do not add water over recommended dosage
- Apply only to sound, prepared substrates

ECOLOGY, HEALTH AND SAFETY

GISCODE: ZP 1

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data. Further notes and information data sheets on product safety and disposal can be found on the Internet at www.sika.de.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete:

The concrete shall be thoroughly clean, free from dust, loose material, surface contamination and materials which reduce bond or prevent suction or wetting by repair materials. De-laminated, weak, damaged and deteriorated concrete and where necessary sound concrete shall be removed by suitable means.

Steel Reinforcement:

Rust, scale, mortar, concrete, dust and other loose and deleterious material which reduces bond or contributes to corrosion shall be removed. Surfaces shall be prepared using abrasive blast cleaning techniques or high pressure water-blasting to SA 2 (ISO 8501-1) Reference shall be made to EN1504-10 for specific requirements.

MIXING

Sika MonoTop®-910 N can be mixed with a low speed (<500 rpm) hand drill mixer or by hand for a small quantity,
Pour the recommended water in a suitable mixing container. While stirring slowly, add the powder to the water and mix thoroughly at least for 3 minutes.

APPLICATION

As Bonding Primer

Thoroughly pre-wet the prepared substrate a recommended 2 hours before application. Keep the surface wet and do not allow to dry. Before application remove excess water e.g. with a clean sponge. The surface shall appear a dark matt appearance without glistening and surface pores and pits shall not contain water. Using a suitably clean brush, roller or suitable spraying equipment cover the substrate in a thin layer filling all unevenness, pits and pores.

As Reinforcement Corrosion Protection

Using a suitably clean brush or spraying equipment apply a first layer to cover the reinforcement bars approximately 1 mm thick. When first coat is hard to the finger nail apply second layer approximately 1 mm thick. If using a spray method protect substrate from excessive over-spray wiping away any concentrated accumulation and wait until completely dry before to apply repair mortar.

CURING TREATMENT

As reinforcement corrosion protection - protect the fresh mortar immediately from premature drying and contamination using an appropriate curing method

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened material can only be mechanically removed.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Deutschland GmbH

Kornwestheimer Straße 103 - 107
D - 70439 Stuttgart
Telefon: 0711/8009-0
Telefax: 0711/8009-0
E-Mail: info@de.sika.com
www.sika.de



PRODUCT DATA SHEET

Sika MonoTop®-910 N
February 2021, Version 01.01
020302020010000050

SikaMonoTop-910N-en-DE-(02-2021)-1-1.pdf