

PRODUCT DATA SHEET

Sikaflex®-271 + SikaBooster® P-50

Booster accelerated glazing adhesive

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base	Polyurethane
Color (CQP001-1)	Black
Cure mechanism	Moisture-curing ^A
Density (uncured)	Adhesive 1.18 kg/l SikaBooster® P-50 1.10 kg/l
Booster content	by volume 2.0 % by weight 1.9 %
Non-sag properties	Very good
Application temperature	ambient 10 – 45 °C
Open time (CQP526-1)	10 minutes ^B
Early tensile lap-shear strength (CQP046-1 / ISO 4587)	See table 1
Shrinkage (CQP014-1)	1 %
Shore A hardness (CQP023-1 / ISO 48-4)	65
Tensile strength (CQP036-1 / ISO 527)	7 MPa
Elongation at break (CQP036-1 / ISO 527)	350 %
Tear propagation resistance (CQP045-1 / ISO 34)	10 N/mm
Tensile lap-shear strength (CQP046-1 / ISO 4587)	5 MPa
Service temperature (CQP513-1)	-40 – 90 °C 4 hours 120 °C 1 hour 140 °C
Shelf life (CQP016-1)	Adhesive 6 months ^C SikaBooster® P-50 9 months ^C
Mixer	Statomix MS13/18 G small volume Statomix MS06/18 T

CQP = Corporate Quality Procedure

^{A)} provided by SikaBooster® P-50^{B)} 23 °C / 50 % r. h.^{C)} storage below 25 °C

DESCRIPTION

Sikaflex®-271 + SikaBooster® P-50 is an accelerated elastic polyurethane adhesive system for glazing applications. Suited for bonding materials relevant for direct glazing such as paints, glass, ceramic frits, painted and e-coated surfaces in commercial-vehicle production.

Sikaflex®-271 + SikaBooster® P-50 is compatible with Sika's black-primerless bonding process.

Owing to the use of SikaBooster® it cures largely independently of atmospheric conditions.

PRODUCT BENEFITS

- Accelerated curing and adhesion build-up
- Very good application properties
- Suitable for automated application
- Low climate dependency of the curing speed with Sika® Booster Technology
- High mechanical strength
- Solvent-free

AREAS OF APPLICATION

Sikaflex®-271 + SikaBooster® P-50 is designed especially for manual and automated direct-glazing application out of bulk packaging where a fast build-up of adhesion and strength is required.

The use of SikaBooster® P-50 provides rapid attainment of strength and early adhesion development.

Seek manufacturer's advice and perform tests on original substrates before using Sikaflex®-271 + SikaBooster® P-50 on materials prone to stress cracking.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

PRODUCT DATA SHEET

Sikaflex®-271 + SikaBooster® P-50

Version 06.02 (08 - 2025), en_DE

012001232710901050

CURE MECHANISM

Sikaflex®-271 + SikaBooster® P-50 cures by reaction with moisture provided by SikaBooster® P-50 and largely independent from atmospheric moisture. For typical strength build-up data see table below.

Time [h]	Tensile lap-shear strength at 23 °C [MPa]
1	1.5
2	4
3	5

Table 1: Strength build-up Sikaflex®-271 + SikaBooster® P-50

CHEMICAL RESISTANCE

Sikaflex®-271 + SikaBooster® P-50 is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

METHOD OF APPLICATION

Surface preparation

Surfaces must be clean, dry and free from grease, oil and dust. Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond. All pre-treatment steps must be confirmed by preliminary tests on original substrates considering specific conditions in the assembly process.

Application

Sikaflex®-271 + SikaBooster® P-50 needs to be processed with an adequate dispensing system. The mixer type needs to be respected (see table Typical Product Data). Sikaflex®-271 + SikaBooster® P-50 can be applied between 10 °C and 45 °C but changes in reactivity and application properties have to be considered. The optimum temperature for substrate and sealant is between 15 °C and 25 °C.

To ensure a uniform thickness of the bondline it is recommend to apply the adhesive in form of a triangular bead (see figure 1).




Figure 1: Recommended bead configuration

The open time is significantly shorter in hot and humid climate. The glass must always be joint within the open time. Never install a glass after the product has built a skin.

As a rule of thumb, a change of + 10 °C reduces the open time by half.

For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

Removal

Uncured Sikaflex®-271 + SikaBooster® P-50 can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water. Do not use solvents on skin.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- Sika Pre-treatment Chart
- General Guidelines
- For 1-component Polyurethanes
- Bonding and Sealing with 1-component Sikaflex®

PACKAGING INFORMATION

Sikaflex®-271

Pail	23 l
Drum	195 l

SikaBooster® P-50

Unipack	600 ml
Pail	23 l

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PRODUCT DATA SHEET

Sikaflex®-271 + SikaBooster® P-50
Version 06.02 (08 - 2025), en_DE
012001232710901050

Sika Deutschland CH AG & Co KG

Industry
Stuttgarter Straße 139
72574 Bad Urach
Tel. +49 7125 940-7692
verkauf.industry@de.sika.com
www.sika.de

