

## PRODUCT DATA SHEET

# SikaTack® Panel

## 1-COMPONENT POLYURETHANE FOR PANEL BONDING IN VENTILATED FACADES

### TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base	1-component polyurethane
Color (CQP001-1)	Ivory
Cure mechanism	Moisture-curing
Density (uncured)	1.1 kg/l
Non-sag properties	Good
Application temperature	ambient 5 – 40 °C
Skin time (CQP019-1)	35 minutes <sup>A</sup>
Curing speed (CQP049-1)	(See diagram)
Shore A hardness (CQP023-1 / ISO 48-4)	45
Tensile strength (CQP036-1 / ISO 527)	2.5 MPa
Elongation at break (CQP036-1 / ISO 527)	500 %
Tear propagation resistance (CQP045-1 / ISO 34)	7 N/mm
Service temperature (CQP509-1 / CQP513-1)	-40 – 90 °C
Shelf life	12 months <sup>B</sup>

CQP = Corporate Quality Procedure

<sup>A</sup>) 23 °C / 50 % r. h.<sup>B</sup>) storage below 25 °C

### DESCRIPTION

SikaTack® Panel is a non-sag, 1-component polyurethane of paste-like consistency for structural joints in ventilated facades and interior wall cladding between the vertically installed substructure and the panel that will be subjected to high dynamic and static stresses. It cures on exposure to atmospheric humidity. SikaTack® Panel is part of the SikaTack® Panel system for the economic, concealed fixing of ventilated facades.

### PRODUCT BENEFITS

- Elastic fixing system, vibration and movement absorbing
- SikaTack® Panel is approved from "Deutsches Institut für Bautechnik, DIBT"
- Provides creative opportunities for facade design
- Uniform tension over the whole facade panel (no stress points)
- Withstands high dynamic and static stresses
- 1-part product, ready to use
- Weathering resistant
- Bonds well to a wide variety of substrates

### AREAS OF APPLICATION

SikaTack® Panel is suitable for structural joints in ventilated facades and cladded interior walls between the vertically installed substructure and the facade panel that will be subjected to dynamic and static stresses. Suitable substrates are anodized and coated aluminum, metal composite, high pressure laminate and ceramic materials. This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

### PRODUCT DATA SHEET

SikaTack® Panel  
Version 04.01 (04 - 2023), en\_DK  
012036210019001000

## CURE MECHANISM

SikaTack® Panel cures by reaction with atmospheric moisture. At low temperatures the water content of the air is generally lower and the curing reaction proceeds somewhat slower (see diagram 1).




Diagram 1: Curing speed SikaTack® Panel

## METHOD OF APPLICATION

### Surface preparation

Surfaces must be clean, dry and free from grease, oil, dust and contaminants. Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond.

### Application

The standard geometry for bonding façade panels is at least 12 x 3 mm. The supplied nozzle (10 x 8 mm) ensures proper dimension of the compressed bead (see figure below).




Figure 1: Recommended bead configuration

The optimum temperature for substrate and adhesive is between 15 °C and 25 °C. Do not apply at temperatures below 5 °C or above 40 °C.

To avoid condensation on the surfaces, the temperature of the bonding components (e.g. façade panels, sub-frames) must be at least 3 °C higher than the dew point of the air.

The skin time is significantly shorter in hot and humid climate. The panel must always be installed within 75 % of the skin time determined under local climate conditions (see General Guideline "SikaTack® Panel System"). Never join bonding parts if the adhesive has built a skin. SikaTack® Panel can be processed with hand, pneumatic or electric driven piston guns.

### Removal

Uncured SikaTack® Panel can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically.

Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

### Application limits

SikaTack® Panel used for panel bonding is always used in conjunction with SikaTack® Panel Fixing Tape. SikaTack® Panel Fixing Tape ensures the correct joint thickness and keeps the bonded panels initially in place. By curing SikaTack® Panel builds up strength and takes over the long-term load bearing.

SikaTack® Panel Fixing Tape is not a structural component.

### FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- General Guideline SikaTack® Panel System

## PACKAGING INFORMATION

Cartridge*	300 ml
Unipack	600 ml

\* Not on stock in DK

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

## DISCLAIMER

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

## PRODUCT DATA SHEET

SikaTack® Panel  
Version 04.01 (04 - 2023), en\_DK  
012036210019001000

Sika Danmark A/S  
Hirsemarken 5  
3520 Farum  
Tlf. +45 48 18 85 85  
www.sika.dk

