

## PRODUCT DATA SHEET

# Sikafloor® Marine-107

Ultra lightweight self-leveling primary deck covering mortar for interior decks

**TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)**

<b>Chemical base</b>	Polymer modified cement mortar
<b>Color</b>	Grey
<b>Cure mechanism</b>	Hydraulic
<b>Density</b>	fresh 1 kg/l cured 0.7 kg/l
<b>Mixing ratio</b>	per 12 kg bag 6.5 – 6.8 liters
<b>Substrate temperature</b>	5 – 30 °C
<b>Coverage</b>	per 12 kg bag at layer thickness 1 mm 17 m <sup>2</sup>
<b>Working time (CQP599-9)</b>	20 minutes <sup>A</sup>
<b>Ready to walk on (CQP600-3)</b>	depending on humidity and ventilation 3 hours <sup>A</sup>
<b>Compressive strength (CQP599-2)</b>	11 MPa <sup>B</sup>
<b>Flexural strength (CQP599-1)</b>	3 MPa <sup>B</sup>
<b>Modulus of elasticity in compression (CQP599-6 / EN 13412)</b>	3 GPa <sup>B</sup>
<b>Linear shrinkage (CQP599-5)</b>	0.03 % <sup>B</sup>
<b>Shelf life</b>	12 months <sup>C</sup>

CQP = Corporate Quality Procedure

<sup>A)</sup> 23 °C / 50 % r. h.<sup>B)</sup> after 28 days<sup>C)</sup> stored in a dry, cool place below 25 °C
**DESCRIPTION**

Sikafloor® Marine-107 is a 1-component ultra-light weight self-leveling mortar based on polymer modified cement.

Sikafloor® Marine-107 is tested according to FTP Code system and approved according to the IMO Marine Equipment Directives.

**PRODUCT BENEFITS**

- Ultra-light weight leveling mortar
- Good leveling properties in thin layers
- Can be pumped
- One component, ready to mix
- Easy to apply

**AREAS OF APPLICATION**

Sikafloor® Marine-107 is applied on interior decks, to level the surface prior to the application of deck finishing materials such as carpets and vinyl. It is suitable for application in throughout the accommodation areas.

This product is suitable for experienced professional users only. Test with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

**PRODUCT DATA SHEET**

Sikafloor® Marine-107

Version 04.01 (03 - 2023), en\_FI

019319000194001000

## CURE MECHANISM

Sikafloor® Marine-107 cures by way of hydraulic curing.

## METHOD OF APPLICATION

### Surface preparation

For leveling applications, the surface has to be clean, free from dust, grease, oils and other substances, which may impair adhesion. Rust has to be removed with a steel brush or other appropriate means, followed by vacuum cleaning.

The surface has to be primed with Sikafloor® Marine Primer C using a long hair roller. After drying of the Sikafloor® Marine Primer C, Sikafloor® Marine-107 may be applied. Sikafloor® Marine-107 applications on aluminum or zinc rich shop primer coated decks, require a tie coat of SikaCor® ZP Primer or another suitable tie coat prior the priming step with Sikafloor® Marine Primer C.

### Mixing process

One bag of Sikafloor® Marine-107 is mixed with 6.5 to 6.8 liters cold potable water. The mixing time with a drilling machine and proper mixing paddles is approx. 5 minutes (not higher than 400 rpm).

Ensure the powder is mixed completely (bottom and side walls of the bucket).

### Application

Apply the mortar with a steel board or a straight edge. Sikafloor® Marine-107 can also be applied by pinrake.

Sikafloor® Marine-107 has to be applied within 20 minutes after mixing. At temperatures above 30 °C the open time will be reduced to 10 minutes or less.

If applied in thickness less than 3 mm the self-leveling capability will be reduced.

For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

## Curing

After application, the finished areas have to be protected against direct heat (e.g. cutting or welding from beneath), sunlight and draught during the curing process for at least 12 hours.

Before Sikafloor® Marine-107 is covered with dense materials such as vinyl, etc., ensure that the remaining moisture level is below 4 %.

Test procedure to determine the dryness (according ASTM D 4263): put a PE-plastic foil 1 m x 1 m on the surface of the applied mortar floor, tape the perimeter and leave for one day. The curing is complete if there is no water condensation on the foil or a visible color difference between covered and uncovered surface.

## Removal

Excess material can best be removed before curing with a trowel wipe or water.

Fresh Sikafloor® Marine-107 may be removed from tools and equipment with water. Once cured, the material can only be removed mechanically.

Exposed hands and skin shall be washed immediately with water. Use a suitable skin protection hand cream.

## Application limits

For applications on slooping surfaces > 1 % contact the Technical Department of Sika Industry.

## FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheet
- Application Manual  
Sikafloor® Marine-107

## PACKAGING INFORMATION

Bag	12 kg
-----	-------

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

## DISCLAIMER

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

## PRODUCT DATA SHEET

Sikafloor® Marine-107  
Version 04.01 (03 - 2023), en\_FI  
019319000194001000

Oy Sika Finland Ab  
TM Industry  
PL 49, Koskelontie 23 C  
02921 Espoo  
Puh. 09-511 431  
www.sika.fi

