

## PRODUCT DATA SHEET

## Sika® InjectoCem-190

## Micro cement injection grout

## DESCRIPTION

2-part, mineral injection grout based on microcement binders with added corrosion inhibitors (d<sub>95</sub> < 9.5 μm).

## USES

- Injection of Sika® Injectoflex® Systems Typ DI-1 and SikaFuko® injection hoses
- Filling of voids
- Final, rigid, cementitious sealing of cracks while simultaneously treating corroding or corrosion-prone reinforcing steel in concrete and mortar

## FEATURES

- Structural grouting of cracks
- Corrosion protection of embedded reinforcement
- Deep penetration of narrow cracks in concrete and mortar
- Good flow properties

## PRODUCT INFORMATION

Composition	Modified micro cement		
Packaging	Part A:	2 * 2.50 kg (Bag)	Powder component
	Part B:	3.25 kg (PE-Bidon)	Liquid component
	Part A + B:	8.25 kg (Pail)	Ready mix unit
Shelf life	In unopened original packaging: 12 months from date of production		
Storage conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.		
Density	Part A + B:	~ 1.70 kg/l (+20 °C)	
Viscosity	~ 100 mPa·s	(+20 °C)	

## TECHNICAL INFORMATION

Compressive strength	1 day:	~ 30 MPa
	7 days:	~ 35 MPa
	28 days:	~ 37 MPa
Modulus of elasticity in compression	28 days:	~ 9 600 MPa
Flexural-strength	28 days:	~ 2 MPa

## APPLICATION INFORMATION

Mixing ratio	Part A : B:	1 : 0.65 (by weight)
Yield	Pre-batched unit of 8.25 kg gives:	~ 5 l of injection grout
Ambient air temperature	Min. +5 °C, max. +35 °C	
Substrate temperature	Min. +5 °C, max. +35 °C	
Pot Life	~ 30 minutes The pot life can be doubled by adding 1 % Sikament®-212 A.  Keep in movement when not in use.	

### BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

### ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

### APPLICATION INSTRUCTIONS

#### SUBSTRATE PREPARATION

The substrate must be sound, clean, free of oil and grease, old coatings and other contaminations.

For good adhesion, pre-treat the substrate with high pressure water or mechanically.

Use air pressure to remove dust from cracks.

#### MIXING

Sika® InjectoCem-190 is delivered in two precisely matched components. If required, a maximum of 0.2 l water can be added.

Place the liquid part B in a suitable mixing vessel. Mix with colloidal mixer at approx. 2 800 rpm and add the powder part A slowly and continuously. Mix the suspension thoroughly for at least 3 minutes.

Subsequently, pour the injection material directly into the pump or keep ready in a clean container.

### APPLICATION METHOD / TOOLS

The injection material can be injected with commercially available equipment designed for cement injections (injection pressure 3 - 8 bar).

For vertical injection sections, inject from bottom to top.

If dry concrete has to be injected, it is recommended to pre-wet the concrete with water under light pressure.

In order to enable post-injections, the freshly injected section of the SikaFuko® systems (or the injection packers) must be thoroughly rinsed.

#### CLEANING OF EQUIPMENT

Clean tools with water immediately after use. Hardened material can only be removed mechanically.

### LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika Gulf B.S.C. (c)

Tel: +973 177 38188  
Email: [info@bh.sika.com](mailto:info@bh.sika.com)  
Sika Kuwait Cons. Mat. & Paints Co WLL  
Tel: +965 22 282 296  
Email: [sika.kuwait@kw.sika.com](mailto:sika.kuwait@kw.sika.com)  
Web: [gcc.sika.com](http://gcc.sika.com)

### Sika UAE LLC

Sika MB Construction Chemicals LLC  
Sika International Chemicals LLC  
Tel: +971 4 439 8200  
Email: [info@ae.sika.com](mailto:info@ae.sika.com)  
Web: [gcc.sika.com](http://gcc.sika.com)

### Sika Saudi Arabia Limited

Sika Construction Chemicals for  
Manufacturing LLC  
Riyadh / Jeddah / Dammam / Rabigh  
Tel: +966 9200 22167  
Email: [info@sa.sika.com](mailto:info@sa.sika.com)  
Web: [gcc.sika.com](http://gcc.sika.com)

### Sika LLC - Oman

Sika MB LLC  
Tel: +968 22 826 500  
Email: [info@om.sika.com](mailto:info@om.sika.com)  
Web: [gcc.sika.com](http://gcc.sika.com)



ISO 9001, 14001, 45001 – SGS  
Sika MB LLC  
Sika International Chemicals LLC  
Sika Gulf B.S.C. (c)  
ISO 9001, 14001 – SGS  
Sika Saudi Arabia Limited  
ISO 9001, 14001 – TÜV  
Sika MB Construction Chemicals LLC  
Sika Construction Chemicals  
for Manufacturing LLC  
ISO 9001 – LMS  
Sika MB LLC

All products are supplied under  
a management system certified  
to conform to the requirements  
of the quality, environmental  
and occupational health &  
safety standards ISO 9001, ISO  
14001 and ISO 45001.



### Product Data Sheet

#### Sika® InjectoCem-190

February 2025, Version 04.02  
02070705260000027

SikalnjectoCem-190-en-AE-(02-2025)-4-2.pdf