

PRODUCT DATA SHEET

Sikalastic®-1K

ONE-COMPONENT CEMENTITIOUS MORTAR, FIBRE-REINFORCED FOR FLEXIBLE WATERPROOFING AND CONCRETE PROTECTION



DESCRIPTION

Sikalastic®-1K is a one-component, crack-bridging, fibre-reinforced mortar, based on cement modified with special alkali-resistant polymers. Sikalastic®-1K is suitable for application by brush or trowel. Suitable for use in tropical and hot climatic conditions.

USES

- Flexible waterproofing and protection of concrete structures including tanks, basins, pipes etc.
- Waterproofing of bathrooms, showers, terraces, balconies, swimming pools before the application of ceramic tiles bonded with adhesives
- Waterproofing of external concrete wall surfaces to be backfilled in ground
- Inside waterproofing of negative water pressure of walls and floors in basements
- Flexible protection coating for reinforced concrete structures against the effects of freeze-thaw and carbon dioxide attack to improve durability

CHARACTERISTICS / ADVANTAGES

- One-component product, only water needs to be added
- Adjustable consistency, easy to apply by brush or trowel
- Good sag resistance and easy to apply, even on vertical surfaces
- Good crack-bridging ability
- Very good adhesion on many substrates including concrete, cement mortars, stone, masonry
- Can be applied on damp substrates

APPROVALS / CERTIFICATES

- CE-marking and Declaration of Performance as surface protection product for concrete - coating for ingress protection, moisture control and increasing resistivity according to EN 1504-2:2004, based on certificate of factory production control issued by notified factory production control certification body and type testing.

PRODUCT INFORMATION

Composition	Cement modified with alkali resistant polymers, selected aggregates, fine fillers admixtures, additives and fibres.
Packaging	18 kg bags
Appearance / Colour	Light grey
Shelf life	12 months from date of production
Storage conditions	Store properly in the original packaging, in cool and dry conditions. Protect from water.
Maximum Grain Size	D _{max} : ~0,3 mm

TECHNICAL INFORMATION

Tensile Adhesion Strength	≥ 1.0 N/mm ² Value obtained with a total layer thickness of 2 mm in two layers with 22 % water	(EN 1542)
Crack Bridging Ability	> 0,50 mm (Class A 3, +23 °C) > 0,50 mm (Class A 3, -10 °C) Values obtained with a total layer thickness of 2 mm in two layers with 22 % water	(EN 1062-7) (EN 1062-7)
Freeze Thaw De-icing Salt Resistance	≥ 0.8 N/mm ² Value obtained with a total layer thickness of 2 mm in two layers with 22 % water	(EN 13687-1)
Permeability to Carbon Dioxide	S _D ≥ 50 m Value obtained with a total layer thickness of 2 mm in two layers with 22 % water	(EN 1062-6)

APPLICATION INFORMATION

Mixing Ratio	Application Method	Water dosage
	By brush	~4,7 litres water per 18 kg bag
	By trowel	~4,0 litres water per 18 kg bag
Fresh Mortar Density	~1,5 kg/l	
Consumption	This depends on the substrate roughness; as a guide: ~1,5 kg/m ² /mm. This figure is theoretical and does not include for any additional material required due to surface porosity, surface profile, variations in level and wastage etc..	
Layer Thickness	2 mm with constant dry film thickness, applied in minimum 2 layers. Maximum recommended thickness per layer is 2 mm when applied by trowel and 1 mm when applied by brush.	
Ambient Air Temperature	5 °C min. / 35 °C max.	
Substrate Temperature	5 °C min. / 35 °C max.	
Pot Life	~30 min (+20 °C)	
Waiting Time / Overcoating	Sikalastic®-1K must be completely hardened before over-coating or water contact. Guide for waiting times at the following temperatures:	
		+20 °C
	Covering by tiles	~2 days
	Immersion in water	~2 days
	Contact with drinkable water	~15 days
	Times will vary due to ambient and substrate humidity.	

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Substrates must be structurally sound, clean, dry and free of all contaminants such as dirt, oil, grease, cement laitance, coatings and other surface treatments etc.

Clean surfaces by blast cleaning, high-pressure water-jetting (400 bar), wire-brushing, grinding etc., in order to remove all previous coatings, any traces of grease, rust, release agents, cement laitance and any other material which could reduce adhesion. All dust deposits from this preparation must also be removed i.e. by vacuum.

Repair concrete substrates, if necessary, with an appropriate cementitious mortar from the SikaTop®, SikaRep® or Sika MonoTop® range of repair materials. The substrate shall be adequately dampened before

application. The surface shall not be moist to the touch and shall not be the dark matte (saturated surface dry) appearance.

MIXING

Sikalastic®-1K can be mixed with a low speed (~ 500 r/min) hand drill mixer, adding the right quantity of water according to the respective application. Once a homogeneous mix is obtained, continue mixing for 3–4 min. The mortar must be homogeneous and lump free. Do not add any additional water or other ingredients. Each bag must be entirely mixed, to avoid faulty particle size distribution of aggregates contained in the powder component.

APPLICATION

Special Requirements:

All connections between the substrate and pipe

entries, plant and equipment, light switches etc., must be sealed and watertight. Joints in concrete, pipes or anywhere else in the structure must also be sealed and made watertight.

Use coved details at the floor/wall junctions.

Apply Sikalastic®-1K by:

- spatula/roller: Exerting good and even pressure onto the substrate;
- brush: In 2 directions (diagonally opposite / cross-wise);
- mechanical spray: Refer to Sika Technical Department for details

The optimum waterproofing performance is obtained by applying Sikalastic®-1K by trowel in at least 2 layers, to a total thickness of at least 2 mm.

Application by brush must be undertaken with the maximum attention to uniformly covering the whole surface. The maximum recommended thickness for these methods of application is 1 mm per layer. In these situations, the application of min. 2–3 layers is required (subsequent layers must be applied cross-wise).

Wait until the first layer is dry before applying subsequent layers.

The application shall cover the whole surface of the substrate in a uniform thickness.

Sikalastic®-1K cannot be smoothed using float or sponge trowel. It is possible to smooth the surface as soon as the curing of the product is complete by light abrasion techniques.

CLEANING OF EQUIPMENT

Tools should be thoroughly cleaned with water before the material has set. Hardened mortar can only be removed mechanically.

IMPORTANT CONSIDERATIONS

- Sikalastic®-1K shall not be smoothed using a float or trowel.
- Protect from rain for at least 24–48 h after application.
- Avoid direct contact with chlorinated water i.e. in swimming pools, by using suitable protection (eg. tiles).
- Avoid application in direct sun light, when rain is imminent or in strong winds.
- Setting time can be influenced by high relative humidity, particularly in closed rooms or basements. The use of adequate ventilation is recommended.
- Sikalastic®-1K is permeable to water vapour and does not form a vapour barrier for resin based systems not permeable to gas.
- If a solvent based paint is to be applied on Sikalastic®-1K, carry out preliminary testing in order to ensure the solvents do not attack and damage the waterproofing layer.
- When used in contact with drinking water, ensure Sikalastic®-1K and all associated Sika® products comply with the local regulations and project specifications for drinking water contact.
- Before contact with drinking water, ensure the Sikalastic®-1K is completely hardened respecting the

suggested waiting times and wash carefully to remove dust, loose material or stagnant water, according to local regulations.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait
Tel: +973 177 38188
sika.gulf@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF

UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

SIKA SAUDI ARABIA

Riyadh / Jeddah / Damman
Tel: +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd,
Sika Qatar LLC
ISO 14001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd
OHSAS: Sika UAE LLC,
Sika Gulf B.S.C. (c)

All products are supplied
under a management
system certified to conform
to the requirements of the
quality, environmental and
occupational health &
safety standards ISO 9001,
ISO 14001 and OHSAS
18001.

Product Data Sheet

Sikalastic®-1K

December 2017, Version 01.01
020701010010000180

Sikalastic-1K-en-AE-(12-2017)-1-1.pdf

