

## PRODUCT DATA SHEET

# SikaBiresin® SC258

LIGHT WEIGHT EPOXY MODELING PASTE - DENSITY < 0.60

## APPLICATIONS

- Direct hand modeling of small volumes
- Application on approximate core up to 40 mm for large volumes
- Large light weigh models for all Industry
- Light weight checking fixture, machining supports

## MAIN PROPERTIES

- 1:1 mix ratio by weight or volume
- Friendly use with tinted components
- Mix by hand or planetary mixing machine
- Stick on itself for thick applications

## DESCRIPTION

Basis	Two-component-epoxy-system
Component A	<b>SikaBiresin® SC258</b> , pasty epoxy resin, white
Component B	<b>SikaBiresin® SC258</b> , pasty hardener, light brown

## PHYSICAL PROPERTIES

Components		Resin (A)	Hardener (B)
		<b>SikaBiresin® SC258</b>	<b>SikaBiresin® SC258</b>
Viscosity, 25 °C	mPa.s	paste	paste
Density 25 °C	ISO 1675-75	0.48	0.55
Mixing ratio	in parts by weight	100	100
	in parts by volume at 25 °C	100	100
		Mixture	
Colour		Light brown	
Viscosity, 25 °C	mPa.s	paste	
Potlife, 25 °C, 250 g	min	65	
Maximum advised thickness	mm	40	

## MECHANICAL PROPERTIES

(approx. values at 23 °C, obtained on standard specimens after curing 16 h at 40 °C)

Density, 23 °C	ISO 2781		0.57
Shore hardness	ISO 868	Shore D1 at 23°C	60
		Shore D15 at 23°C	58
Compressive yield strength	ISO 604	MPa	23

## THERMAL AND SPECIFIC PROPERTIES

(approx. values at 23 °C, obtained on standard specimens after curing 16 h at 40 °C)

Glass transition temperature	ISO 11359-2	°C	51
Coefficient of thermal expansion (CTE) [+10 °C to +50 °C]	ISO 11359-2	10 <sup>-6</sup> K <sup>-1</sup>	48
Hardening time before machining		h	12 - 18
Complete curing at 23°C		d	2

## PACKAGING UNITS

- |   |                   |
|---|-------------------|
| ■ Resin (A), <b>SikaBiresin® SC258</b>    | 5,0 kg; 10 kg net |
| ■ Hardener (B), <b>SikaBiresin® SC258</b> | 5,0 kg; 10 kg net |

## PROCESSING DATA

- The material, processing and mould temperature must be at least 18 – 25 °C.
- Mix resin + hardener by hand up to 500 gr mixing. For bigger use a mixer
- As soon as the colour is uniform you can apply the resin.
- On smooth cores apply first a thin layer by spatula (bonding layer)
- Slick the surface with alcohol or water to get it smooth.

## STORAGE CONDITIONS

Shelf life	■ Resin (A), <b>SikaBiresin® SC258</b>	12 months
	■ Hardener (B), <b>SikaBiresin® SC258</b>	12 months
Storage temperature	■ Resin (A), <b>SikaBiresin® SC258</b>	18 – 25 °C
	■ Hardener (B), <b>SikaBiresin® SC258</b>	18 – 25 °C
Opened packagings	■ Containers must be closed tightly immediately after use.	
	■ The residual material needs to be used up as soon as possible.	

## FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Advanced Resins. Copies of the following publications are available on request: Safety Data Sheets

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTICE

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

---

## Contact

---

**SIKA DEUTSCHLAND GMBH**  
Stuttgarter Straße 139  
72574 Bad Urach - GERMANY  
Phone: +49 7125 940 492  
Fax: +49 7125 940 401  
E-Mail: tooling@de.sika.com  
Website: www.sikaadvancedresins.de

**SIKA AUTOMOTIVE FRANCE S.A.S.**  
ZI des Béthunes - 15, Rue de l'Equerre  
95310 Saint-Ouen-l'Aumône  
CS 40444  
95005 Cergy Pontoise Cedex - FRANCE  
Phone: +33 1 34 40 34 60  
Fax: +33 1 34 21 97 87  
E-Mail: advanced.resins@fr.sika.com  
Website: www.sikaadvancedresins.fr

**AXSON TECHNOLOGIES SPAIN, S.L.**  
C/Guardaagullles, 8 – P.I. Congost - 08520  
Les Franqueses del Valles (Barcelona) - SPAIN  
Phone: +34 93 225 16 20  
Fax: +34 93 225 03 05  
E-Mail: spain@axson.com  
Website: www.sikaadvancedresins.es

**AXSON ITALIA S.R.L.**  
Via Morandi 15  
21047 Saronno (Va) – ITALY  
Phone: +39 02 96 70 23 36  
Fax: +39 02 96 70 23 69  
E-Mail: axson@axson.it  
Website: www.sikaadvancedresins.it

**AXSON UK LTD**  
Unit 15 Studlands Park Ind. Estate  
Newmarket Suffolk, CB8 7AU - UNITED KINGDOM  
Phone: +44 1638 660 062  
Fax: +44 1638 665 078  
E-Mail: sales.uk@axson.com  
Website: www.sikaadvancedresins.uk

**SIKA AUTOMOTIVE SLOVAKIA S.R.O.**  
Tovarenska 49  
953 01 Zlate Moravce - SLOVAKIA  
Phone: +421 2 5727 29 33  
Fax: +421 37 3000 087  
E-Mail: SikaAdvancedResins@sk.sika.com  
Website: www.sikaadvancedresins.com

**SIKA ADVANCED RESINS US**  
30800 Stephenson Highway  
Madison Heights, Michigan 48071 - USA  
Phone: +1 248 588 2270  
Fax: +1 248 616 7452  
E-Mail: advanced.resins@us.sika.com  
Website: www.sikaadvancedresins.us

**SIKA AUTOMOTIVE EATON RAPIDS, INC.**  
1611 Hults Drive  
Eaton Rapids, Michigan 48827 - USA  
Phone: +1 517 663 81 91  
Fax: +1 517 663 05 23  
E-Mail: advanced.resins@us.sika.com  
Website: www.sikaadvancedresins.us

**SIKA AUTOMOTIVE MEXICO S.A. DE C.V.**  
Ignacio Ramirez #20 Despacho 202 Col.  
Tabacalera C.P. 06030 CDMX - MEXICO  
Phone: +52 55 5264 49 22  
E-Mail: marketing@axson.com.mx  
Website: www.sikaadvancedresins.mx

**SIKA AUTOMOTIVE SHANGHAI CO. LTD.**  
N°53 Tai Gu Road  
Wai Gao Qiao  
Free Trade Zone, Pudong  
200131 Shanghai - CHINA  
Phone: +86 21 58 68 30 37  
Fax: +86 21 58 68 26 01  
E-Mail: marketing.china@axson.com  
Website: www.sikaaxson.cn

**Sika Ltd.**  
10 F, Shinagawa Intercity Tower B.  
2-15-2 Konan, Minato-ku  
Tokyo 108-6110 - JAPAN  
Phone: +81 3 6433 2314  
Fax: +81 3 6433 2102  
E-Mail: advanced-resins@jp.sika.com  
Website: www.jpn.sika.com

**AXSON INDIA PVT. LTD.**  
Office n°8, Building Symphony C - 3rd Floor  
Range Hills Road  
Bhosale Nagar  
Pune 411 020 - INDIA  
Phone: +91 20 25560 710  
Fax: +91 20 25560 712  
E-Mail: info.india@axson.com  
Website: www.sikaadvancedresins.in