

## PRODUCT DATA SHEET

# Sikaflex®-521 UV

Weathering-resistant STP adhesive sealant with a wide adhesion range

**TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)**

<b>Chemical base</b>		Silane Terminated Polymer
<b>Colour (CQP001-1)</b>		White, grey, black
<b>Cure mechanism</b>		Moisture-curing
<b>Density (uncured)</b>	depending on color	1.4 kg/l
<b>Non-sag properties</b>		Good
<b>Application temperature</b>	ambient	5 – 40 °C
<b>Skin time (CQP019-1)</b>		30 minutes <sup>A</sup>
<b>Curing speed (CQP049-1)</b>		(see diagram)
<b>Shrinkage (CQP014-1)</b>		2 %
<b>Shore A hardness (CQP023-1 / ISO 48-4)</b>		40
<b>Tensile strength (CQP036-1 / ISO 527)</b>		1.8 MPa
<b>Elongation at break (CQP036-1 / ISO 527)</b>		400 %
<b>Tear propagation resistance (CQP045-1 / ISO 34)</b>		5.5 N/mm
<b>Service temperature (CQP513-1)</b>		-50 – 90 °C
	4 hours	140 °C
	1 hour	150 °C
<b>Shelf life (CQP016-1)</b>	cartridge / unipack	12 months <sup>B</sup>
	pail / drum	9 months <sup>B</sup>

CQP = Corporate Quality Procedure

<sup>A</sup>) 23 °C / 50 % r. h.<sup>B</sup>) storage below 25 °C
**DESCRIPTION**

Sikaflex®-521 UV is a weathering-resistant 1-component Silane Terminated Polymer (STP) adhesive / sealant that bonds well to a wide variety of bonding surfaces such as metals, ABS, PC, FRP and wood with usually no need for special pre-treatment. This multipurpose product is suitable for internal and external sealing applications.

**PRODUCT BENEFITS**

- Ageing and weathering-resistant
- Bonds well to a wide variety of substrates without the need for special pre-treatment
- Isocyanate- and solvent-free
- Can be overpainted
- Can be sanded
- Low odour

**AREAS OF APPLICATION**

Sikaflex®-521 UV adheres well to a wide variety of substrates and is suitable for elastic sealing and bonding. Suitable substrate materials include timber, metals, metal primers and paint coatings (2-component systems), ceramic materials and plastics.

This multipurpose product is suitable for internal and external sealing applications. Seek manufacturer's advice and perform tests on original substrates before using Sikaflex®-521 UV on materials prone to stress cracking. This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

**PRODUCT DATA SHEET**

Sikaflex®-521 UV

Version 04.01 (04 - 2022), en\_IE

012201205210001000

## CURE MECHANISM

Sikaflex®-521 UV cures by reaction with atmospheric moisture. At low temperatures the water content of the air is generally lower and the curing reaction proceeds somewhat slower (see diagram 1).




Diagram 1: Curing speed Sikaflex®-521 UV

## CHEMICAL RESISTANCE

Sikaflex®-521 UV is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

## METHOD OF APPLICATION

### Surface Preparation

Surfaces must be clean, dry and free from grease, oil and dust.

Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond. Suggestions for surface preparation may be found on the current edition of the appropriate Sika® Pre-Treatment Chart. Consider that these suggestions are based on experience and have in any case to be verified by tests on original substrates.

## Application

Sikaflex®-521 UV can be processed between 5 °C and 40 °C but changes in reactivity and application properties have to be considered. The optimum temperature for substrate and adhesive sealant is between 15 °C and 25 °C.

Sikaflex®-521 UV can be processed with hand, pneumatic or electric driven piston guns as well as pump equipment. For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

## Tooling and finishing

Tooling and finishing must be carried out within the skin time of the sealant. It is recommended using Sika® Tooling Agent N. Other finishing agents must be tested for suitability and compatibility prior the use.

## Removal

Uncured Sikaflex®-521 UV can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin have to be washed immediately using Sika® Cleaner-350H cleaning towels or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

## FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- Sika® Pre-treatment Chart  
Silane Terminated Polymer
- General Guidelines  
Bonding and Sealing with Sikaflex® and SikaTack®

## PACKAGING INFORMATION

Cartridge	300 ml
Unipack	600 ml
Pail	23 l

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Material Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

## DISCLAIMER

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

## PRODUCT DATA SHEET

Sikaflex®-521 UV  
Version 04.01 (04 - 2022), en\_IE  
012201205210001000

SIKA IRELAND LIMITED  
Ballymun Industrial Estate  
Ballymun  
Dublin 11, Ireland  
Tel: +353 1 862 0709  
Web: www.sika.ie  
Twitter: @SikaIreland

