

PRODUCT DATA SHEET

Sika AnchorFix®-3030

EPOXY BASED HIGH PERFORMANCE CHEMICAL ANCHORING ADHESIVE

DESCRIPTION

Sika AnchorFix®-3030 is an epoxy resin based, 2-part, thixotropic, high performance anchoring adhesive for anchoring threaded rods and reinforcing bars in both cracked and un-cracked concrete dry or damp concrete

USES

Sika AnchorFix®-3030 may only be used by experienced professionals.

Anchoring adhesive for fixing of non-expanding anchors in the following:

Structural work

- Rebar / steel reinforcement anchoring in new and refurbishment works
- Threaded rods
- Bolts and special fastening / fixing systems

Metalwork, carpentry

- Handrails, balustrades and supports
- Railings
- Window and door frames

Substrates

- Concrete (cracked and un-cracked)
- Hollow and solid masonry
- Wood
- Natural and reconstituted stone
- Solid rock

CHARACTERISTICS / ADVANTAGES

BUILDING TRUST

- Long open Time
- Can be used in damp concrete
- High load capacity
- ETA for anchoring in cracked concrete
- ETA for post installed rebar connections
- Seismic tested (C1 & C2)
- Suitable for contact with drinking water
- Fire resistant
- Styrene-free
- Good adhesion to substrate
- Shrinkage-free hardening
- Standard sealant guns can be used (300ml cartridge)
- Low emissions
- Low wastage

ENVIRONMENTAL INFORMATION

 Conformity with LEED v2009 IEQc 4.1: Low-Emitting Materials - Adhesives and Sealants, Report No. G23807C_04

APPROVALS / STANDARDS

- CE Marking and Declaration of Performance to ETAG 001 Part 1 - Anchors in general and Part 5 - Bonded anchors, used as European Assessment Document (EAD)
- CE Marking and Declaration of Performance to ETA 17/0694 - Bonded injection type anchor for use in cracked and uncracked concrete
- Fire Evaluation of Post Installed Rebar Connections CEN EN 1991-1-2, Sika AnchorFix®-3030, CSTB, Test report MRF 26072904/C

PRODUCT INFORMATION

Chemical Base	Epoxy resin		
Packaging	385 ml dual cartridge	12 cartridges per box	
	585 ml dual cartridge	12 cartridges per box	

Product Data Sheet

Sika AnchorFix®-3030December 2019, Version 02.01
020205010030000007

Part B A+B mixed 24 months from date of The product must be str packaging in dry conditi Always refer to packagin A+B mixed ~95 N/mm² (7 days, +20 ~45 N/mm² (7 days, +20 ~23 N/mm² (7 days, +20 ~5500 N/mm² (7 days, + Long term Short term (1–2 hours)	ored in original i	iginal, unopened nperatures betw ~1,5 kg/l C min. / +50 °C r	veen +10	
24 months from date of The product must be sto packaging in dry conditi Always refer to packagin A+B mixed ~95 N/mm² (7 days, +20 ~45 N/mm² (7 days, +20 ~23 N/mm² (7 days, +20 ~5500 N/mm² (7 days, +	ored in original i	con iginal, unopened nperatures betw ~1,5 kg/l C min. / +50 °C r	veen +10	(ASTM D 695 (ASTM D 638 (ASTM D 638 (ASTM D 638
The product must be stopackaging in dry conditing Always refer to packaging A+B mixed ~95 N/mm² (7 days, +20) ~45 N/mm² (7 days, +20) ~23 N/mm² (7 days, +20) ~5500 N/mm² (7 days, +20)	ored in original i	iginal, unopened nperatures betw ~1,5 kg/l C min. / +50 °C r	veen +10	(ASTM D 695 (ASTM D 638 (ASTM D 638 (ASTM D 638
packaging in dry conditi Always refer to packagin A+B mixed ~95 N/mm² (7 days, +20 ~45 N/mm² (7 days, +20 ~23 N/mm² (7 days, +20 ~5500 N/mm² (7 days, +	ons at terng. O°C) O°C) O°C) -20°C)	~1,5 kg/l C min. / +50 °C r	veen +10	(ASTM D 695 (ASTM D 638 (ASTM D 638 (ASTM D 638
~95 N/mm² (7 days, +20 ~45 N/mm² (7 days, +20 ~23 N/mm² (7 days, +20 ~5500 N/mm² (7 days, +	0°C) 0°C) -20°C) -40°	C min. / +50 °C r	max.	(ASTM D 790 (ASTM D 638 (ASTM D 638
~45 N/mm² (7 days, +20 ~23 N/mm² (7 days, +20 ~5500 N/mm² (7 days, + Long term	0°C) 0°C) -20°C) -40°		max.	(ASTM D 790 (ASTM D 638 (ASTM D 638
~45 N/mm² (7 days, +20 ~23 N/mm² (7 days, +20 ~5500 N/mm² (7 days, + Long term	0°C) 0°C) -20°C) -40°		max.	(ASTM D 790 (ASTM D 638 (ASTM D 638
~23 N/mm² (7 days, +20 ~5500 N/mm² (7 days, +	-20 °C) -20 °C)		max.	(ASTM D 638
~5500 N/mm² (7 days, +	-20 °C)		max.	(ASTM D 638
Long term	-40 °		max.	
			max.	(ETAG 001, Part 5
 Sika AnchorFix® Flexible Extensions Sika AnchorFix® Hole Cleaning Brushes Hybrid Sika AnchorFix® Hole Cleaning Brushes Steel Sika AnchorFix® Static Mixers -Nozzles Sika AnchorFix® Straight Extensions Sika AnchorFix® Perforated Sleeves 				
Part A : Part B = 3 : 1 by	volume			
~8 mm max				
Non-sag, including over	head			
+10 °C min. / +40 °C ma	х.			
+5 °C min. / +40 °C max				
Beware of condensation. Substrate temperature during application must be at least +3 °C above dew point.				
+5 °C min. / +40 °C max				
Temperature +35°C to +40°C +30°C to +35°C +25°C to +30°C +20°C to +25°C +15°C to +20°C +10°C to +15°C +5°C to +10°C*	6 minut 8 minut 12 minu 18 minu 25 minu 40 minu	es es ites ites ites	Curing 2 hour 4 hour 6 hour 8 hour 12 hou 18 hou 24 hou	s s s irs
	• Sika AnchorFix® Flexi • Sika AnchorFix® Hole • Sika AnchorFix® Stati • Sika AnchorFix® Stati • Sika AnchorFix® Strai • Sika AnchorFix® Perfo Part A : Part B = 3 : 1 by ~8 mm max Non-sag, including over +10 °C min. / +40 °C max Beware of condensation Substrate temperature dew point. +5 °C min. / +40 °C max Temperature +35°C to +40°C +30°C to +35°C +25°C to +30°C +20°C to +25°C +15°C to +20°C +10°C to +15°C	■ Sika AnchorFix® Cleaning Pump ■ Sika AnchorFix® Flexible Extens ■ Sika AnchorFix® Hole Cleaning I ■ Sika AnchorFix® Hole Cleaning I ■ Sika AnchorFix® Static Mixers -I ■ Sika AnchorFix® Straight Extens ■ Sika AnchorFix® Perforated Slea Part A : Part B = 3 : 1 by volume ~8 mm max Non-sag, including overhead +10 °C min. / +40 °C max. +5 °C min. / +40 °C max. Beware of condensation. Substrate temperature during apple dew point. +5 °C min. / +40 °C max. Temperature Open till +35 °C to +40 °C 8 minut +25 °C to +35 °C 8 minut +25 °C to +25 °C 18 minut +20 °C to +25 °C 25 minut +10 °C to +15 °C 40 minut +5 °C to +10 °C* 150 minut -5 °C to +10 °C* 150 minut	 Sika AnchorFix® Cleaning Pump Sika AnchorFix® Flexible Extensions Sika AnchorFix® Hole Cleaning Brushes Hybrid Sika AnchorFix® Hole Cleaning Brushes Steel Sika AnchorFix® Static Mixers -Nozzles Sika AnchorFix® Straight Extensions Sika AnchorFix® Perforated Sleeves Part A: Part B = 3:1 by volume ~8 mm max Non-sag, including overhead +10 °C min. / +40 °C max. +5 °C min. / +40 °C max. Beware of condensation. Substrate temperature during application must b dew point. +5 °C min. / +40 °C max. Temperature 435°C to +40°C +30°C to +35°C +30°C to +35°C +20°C to +25°C 12 minutes +20°C to +25°C 18 minutes +15°C to +10°C* 40 minutes 150 minutes	■ Sika AnchorFix® Cleaning Pump ■ Sika AnchorFix® Flexible Extensions ■ Sika AnchorFix® Hole Cleaning Brushes Hybrid ■ Sika AnchorFix® Hole Cleaning Brushes Steel ■ Sika AnchorFix® Static Mixers -Nozzles ■ Sika AnchorFix® Straight Extensions ■ Sika AnchorFix® Perforated Sleeves Part A: Part B = 3:1 by volume ~8 mm max Non-sag, including overhead +10 °C min. / +40 °C max. +5 °C min. / +40 °C max. Beware of condensation. Substrate temperature during application must be at leas dew point. +5 °C min. / +40 °C max. Temperature Open time - T _{gel} Curing +35°C to +40°C 8 minutes 2 hour +30°C to +35°C 8 minutes 4 hour +25°C to +30°C 12 minutes 6 hour +20°C to +25°C 18 minutes 8 hour +15°C to +20°C 25 minutes 12 hou +15°C to +15°C 40 minutes 18 hou +5°C to +15°C 40 minutes 24 hour

* Minimum cartridge temperature: +10°C





APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY


Mortar and concrete must be at the required design strength.

Substrate tensile / compressive strengths (concrete, masonry, natural stone) must be confirmed by testing. The anchor hole must always be clean, dry, free from oil and grease etc.


Loose particles must be removed from the holes. Threaded rods and rebar's must be cleaned thoroughly and free from dirt, oil, grease, corrosion products or any other substances and particles which could affect adhesion.

MIXING


Preparing the cartridge: 385 & 585 ml




1.Unscrew the cap



2. Remove the cap



3. Screw on the static mixer



4. Place the cartridge into the application gun ready for use

When the work is interrupted the static mixer nozzle can remain on the cartridge after the gun pressure has been released. If the resin has hardened in the nozzle when work is resumed, a new nozzle must be attached.

Product Data Sheet Sika AnchorFix®-3030

Sika AnchorFix®-3030December 2019, Version 02.01
020205010030000007

APPLICATION METHOD / TOOLS


Anchors in solid masonry/concrete




1. Drill hole with an electric drill to the diameter and depth required. Drill hole diameter must be in accordance with anchor




2. The drill hole must be cleaned with oil free compressed air using an air lance, pressure: 6 Bar (90 psi). Start from the bottom of the hole and clean minimum 2 x until return air stream is free of dust




3. The drill hole must be thoroughly cleaned with the special steel brush (brush at least 2x). The diameter of the brush must be larger than the diameter of the drill hole




4. The drill hole must be cleaned again as stage 2



5. The drill hole must be thoroughly cleaned again as stage 3




6. The drill hole must be cleaned again as stage 2 & 4




7. Pump gun at least 2 x until both parts are extruded as a one consistant colour. Do not use this material. Release the gun pressure and clean the static mixer opening with a cloth






8. Inject the adhesive into the drill hole, starting from the bottom and slowly pull out the static mixer while extruding the resin into the hole. Avoid entrapping air. For deep holes use extension tubing



9. Insert the anchor with a rotary motion into the filled drill hole within the adhesive open time. Some of the adhesive must flow out of the hole



10. During the resin hardening time the anchor must not be moved or loaded

Important Note: Anchors in hollow blocks: Use Sika AnchorFix®-1.

CLEANING OF TOOLS

Clean all tools and application equipment with Sika® Colma Cleaner immediately after use. Hardened material can only be removed mechanically.

FURTHER DOCUMENTS

 For specific information on design refer to: Technical Documentation Sika AnchorFix®-3030 870 43 18

LIMITATIONS

Natural / reconstituted stone and solid rock properties vary particular with regard to strength, composition and porosity. For each application, the suitability of Sika AnchorFix®-3030 must be tested for bond strength, surface staining and discoloration by first applying the product to a sample area before full project application.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika India Pvt. Ltd.

620, Diamond Harbour Road Commercial Complex II Kolkata - 700 034 Tel : +91 33 24472448 Fax : +91 33 23978688

Mail: info.india@in.sika.com





Product Data Sheet
Sika AnchorFix®-3030
December 2019, Version 02.01
020205010030000007

