

**BUILDING TRUST** 

PRODUCT DATA SHEET

# Sikafloor® Marine-570

IMO approved self-levelling 2-component polyurethane decorative resin

# TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Properties		Sikafloor® Marine-570 (A)	Sikafloor® Marine-570 (B)	
Chemical Base		Polyurethane	Isocyanate	
Color (CQP001-1)		Colored	Transparent	
	mixed	Brown colors available (see color design chart)		
Density		1.5 kg/l	1.2 kg/l	
mixed		1.4 kg/l		
Solid Content		100 %		
Mixing Ratio	by weight	79 : 21		
Application Temperature	substrate / climate	15 – 30 °C <sup>A, B</sup>		
Shore D Hardness (CQP023-1 / ISO 48-4)		67		
Tensile Strength (DIN 53504)		20 MPa		
Elongation at Break (DIN 53504)		100 %		
Pot-Life Pot-Life	10 °C	30 minutes		
	20 °C	21 minutes		
	30 °C	18 minutes		
Shelf Life		9 months <sup>C</sup>	12 months <sup>C</sup>	

CQP = Corporate Quality Procedure A) Substrates must be 3 °C above the dew point

B) max. 80 % r.h. C) stored in sealed container in up-right position in a dry place between 5 and 30 °C, protected from direct sunlight

# DESCRIPTION

Sikafloor® Marine-570 is a self-levelling 2-component polyurethane decorative floor resin and part of the Sikafloor® Marine Deco systems.

Sikafloor® Marine-570 has been tested according to FTP Code system and approved according the IMO Marine Equipment Directives.

# **PRODUCT BENEFITS**

- Good working characteristics
- IMO approved
- Good mechanical resistance
- Very low VOC emission
- Solvent-free (ISO 16001-6)
- Longterm elastic

# AREAS OF APPLICATION

Sikafloor® Marine-570 is designed as a component of the Sikafloor® Marine Deco systems. It is designed for mechanical resistant internal flooring in ship and boat construction and as final compound in the Sikafloor® Marine Deco system for interior and exterior use. This product is suitable for experienced professional users only.

Tests with actual substrates and conditions have to be performed ensuring workability, adhesion and material compatibility.

**Sikafloor® Marine-570**Version 03.01 (03 - 2023), en\_MY 012119015704001000

## **CURE MECHANISM**

The curing of Sikafloor® Marine-570 takes place by a chemical reaction of the two components.

Higher temperatures speed up and lower temperatures slow down the curing process.

#### CHEMICAL RESISTANCE

For advice contact the Technical Department of Sika Industry.

#### METHOD OF APPLICATION

## **Surface Preparation**

Sikafloor® Marine-570 is installed as a black primary deck covering and/or as floor covering in all colors.

Metallic decks need to be prepared to SA 2.5 (ISO 8501). Aluminum decks must not be shot blasted. The prepared metallic surfaces need to be clean, free of dirt, grease, oil and loose particles before the SikaCor® ZP Primer is applied. Cementitious substrates have to be mechanically prepared to remove laitance.

Clean the surface and ensure a surface moisture content of  $\leq$  4 % before applying Sikafloor®-150 /-151 primer.

The application area must be protected against weather and direct sunlight.

If IMO is required, get in contact with Sika to choose an appropriate combination of the Sikafloor® Marine Deco system.

# **Mixing Process**

Prior to mixing, stir part A. Add part B and mix continuously for 2 minutes until a homogeneous mix has been obtained.

Pour material into another container and mix again for at least 1 minute.

Use double mixing paddles not higher than 300 rpm to minimize air entrapment.

For areas with cambers or slopes between 1% and 3% use Sikafloor® Marine Liquid PU Thickener. The dosage is between 1% and 2% in weight depending on the actual situation. For areas with higher cambers it may be required to add additional 1% to 2% of Sika® Extender T or Aerosil by weight to the mix. Alternatively, it is possible to reduce the layer thickness and apply multiple layers.

Note: By increasing the viscosity de-airing properties can be affected.

## **Application**

Sikafloor® Marine-570 is poured and spread evenly by means of a notched trowel, flat trowel or pin-rake. In critical areas a spike roller can be used to improve levelling and de-airing. For deeper sections (e.g. unevenness), it might be necessary to pre-level these sections. Ensure the pre-leveled sections have achieved "foot traffic" cure level prior to proceeding.

For liquid application on cambers and slopes multiple applications steps may be needed. Curing speed depends on temperature and layer thickness. Always consider the pot life to keep a wet edge.

Prior to application, always consult the most current Application Manual.

## Curing

Indications regarding curing details see table below.

Tempera- ture	Foot traffic	Light traffic <sup>A</sup>	Full cure
10 °C	24 hours	48 hours	72 hours
20 °C	18 hours	24 hours	60 hours
30 °C	16 hours	18 hours	48 hours

A) food trolleys and light rolling equipments on soft wheels

#### Removal

Uncured Sikafloor® Marine-570 can be removed from tools and equipment with Sika® Colma Cleaner or another suitable solvent. Once cured, the material can only be removed mechanically.

Hands and exposed skin shall be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

# **Application Limits**

Freshly applied Sikafloor® Marine-570 must be protected from moisture, condensation and water for at least 1 days. Uncured material reacts in contact with water (foaming).

## STORAGE CONDITIONS

Both components of Sikafloor® Marine-570 have to be kept between 5 °C and 30 °C in a dry place. Do not expose it to direct sunlight. After opening of the packaging, the contents need to be protected against moisture.

Minimum temperature during transportation is 5 °C.

# **FURTHER INFORMATION**

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

Safety Data Sheet

# PACKAGING INFORMATION

Sikafloor® Marine-570 (A)

Container	15.8 kg			
Sikafloor® Marine-570 (B)				
Container	4.2 kg			

## **BASIS OF PRODUCT DATA**

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## **HEALTH AND SAFETY INFORMATION**

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

#### DISCLAIMER

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Version 03.01 (03 - 2023), en\_MY 012119015704001000

Sika Kimia Sdn. Bhd.

Lot 689, Nilai Industrial Estate, 71800 Nilai, Negeri Sembilan D.K. Malaysia

Phone: +606-7991762 e-mail: info@my.sika.com Website: www.sika.com.my





