

PRODUCT DATA SHEET

Sikaflex®-591

Multifunctional sealant for marine applications

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical Base	Silane Terminated Polymer
Color (CQP001-1)	White, Black, Grey, Brown
Cure Mechanism	Moisture-curing
Density (Uncured)	1.5 kg/l
Non-Sag Properties	Very good
Application Temperature	5 – 40 °C
Skin Time (CQP019-1)	35 minutes ^A
Open Time (CQP526-1)	20 minutes ^A
Curing Speed (CQP049-1)	(see diagram)
Shrinkage (CQP014-1)	1 %
Shore A Hardness (CQP023-1 / ISO 48-4)	45
Tensile Strength (CQP036-1 / ISO 527)	2.2 MPa
Elongation at Break (CQP036-1 / ISO 527)	500 %
Tear Propagation Resistance (CQP045-1 / ISO 34)	15 N/mm
Service Temperature (CQP513-1)	-50 – 80 °C
Shelf Life	12 months ^B

CQP = Corporate Quality Procedure

^{A)} 23 °C / 50 % r. h.^{B)} storage below 25 °C

DESCRIPTION

Sikaflex®-591 is a sealant based on Sika's Silane Terminated Polymer (STP) technology. With its excellent resistance against the harsh maritime weathering conditions it can be used for a wide range of applications. Sikaflex®-591 exceeds common environmental and safety standards and sets a new benchmark from an ecological point of view. Sikaflex®-591 meets the low spread flame requirements (FTP Code Part 5) set out by the International Maritime Organization (IMO).

PRODUCT BENEFITS

- IMO approved
- Exceeds EH&S standards
- Free of isocyanate, solvents, PVC, phthalates and tin catalysts
- Highly elastic
- Excellent weathering stability
- Very good processing and tooling characteristics
- Bonds well to a wide variety of marine substrates

AREAS OF APPLICATION

Sikaflex®-591 is a multipurpose sealant designed for marine applications. It is suitable for elastic, vibration-resistant joint seals and for a wide variety of interior and exterior sealing applications. Sikaflex®-591 bonds well to substrates commonly used in the marine industry. Sikaflex®-591 is not suitable for applications with teak wood and plastics that are prone to stress cracking (e.g. PMMA, PC, etc.). This product is suitable for experienced professional users only. Test with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

PRODUCT DATA SHEET

Sikaflex®-591

Version 03.01 (07 - 2024), en_MY
012201205914001000

CURE MECHANISM

Sikaflex®-591 cures by reaction with atmospheric moisture. At low temperatures the water content of the air is generally lower and the curing reaction proceeds somewhat slower (see diagram 1).




Diagram 1: Curing speed Sikaflex®-591

CHEMICAL RESISTANCE

Sikaflex®-591 is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

METHOD OF APPLICATION

Surface Preparation

Surfaces must be clean, dry and free from grease, oil and dust.

Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond. Suggestions for surface preparation may be found on the current edition of the appropriate Sika® Pre-treatment Chart. Consider that these suggestions are based on experience and have in any case to be verified by tests on original substrates.

Application

Sikaflex®-591 can be processed between 5 °C and 40 °C but changes in reactivity and application properties have to be considered. The optimum temperature for substrate and sealant is between 15 °C and 25 °C. Sikaflex®-591 can be processed with hand, pneumatic or electric driven piston guns.

In case Sikaflex®-591 could get in contact with polyurethane ensure that those products are cured or wait at least 24 hours prior to seal.

Tooling and Finishing

Tooling and finishing must be carried out within the skin time of the product. It is recommended using Sika® Tooling Agent N. Other finishing agents must be tested for suitability and compatibility prior the use.

Removal

Uncured Sikaflex®-591 can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water. Do not use solvents on skin!

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- General Guidelines
 - Bonding and Sealing with 1-component Sikaflex®
- Sika® Pre-Treatment Chart
 - For Sealing and Bonding in Marine Applications

PACKAGING INFORMATION

Cartridge	300 ml
Unipack	600 ml

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences

in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PRODUCT DATA SHEET

Sikaflex®-591

Version 03.01 (07 - 2024), en_MY
012201205914001000

Sika Kimia Sdn. Bhd.

Lot 689, Nilai Industrial Estate,
71800 Nilai, Negeri Sembilan D.K.
Malaysia
Phone: +606-7991762
e-mail: info@my.sika.com
Website: www.sika.com.my

