

BUILDING TRUST

PRODUCT DATA SHEET

Sikafloor® Marine-599

Self-leveling decorative resin

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Book at the			ou (I @	
Properties		Sikafloor® Marine-599 (A)	Sikafloor® Marine-599 (B)	
Chemical base		Polyurethane	Isocyanate	
Color (CQP001-1)		Colored	Transparent	
mix	ĸed	Various colors available (see color design chart)		
Density		1.5 kg/l	1.2 kg/l	
mix	ĸed	1.4 kg/l		
Solid content		100 %		
Mixing ratio by wei	ght	75 : 25		
Application temperature substrate / clima	ate	15 – 30 °C ^{A, B}		
Shore A hardness (CQP023-1 / ISO 48-4)		84		
Tensile strength (DIN 53504)		8 MPa		
Elongation at break (DIN 53504)		65 %		
Pot-life 10	°C	120 minutes		
20	°C	90 minutes		
30	°C	45 minutes		
Shelf life		9 months ^c	12 months ^C	

CQP = Corporate Quality Procedure

DESCRIPTION

Sikafloor® Marine-599 is a self-levelling aliphatic 2-component polyurethane decorative floor resin. It is part of the Sikafloor® Marine Deco system for exterior use.

If Sikafloor® Marine-599 needs to be accelerated, Sikafloor® Marine-001 or -002 can be used.

PRODUCT BENEFITS

- Good application characteristics
- Very UV stable (non yellowing)
- Decorative designs solutions
- Very low VOC emission
- Solvent-free
- Longterm elastic
- Acceleration option available

AREAS OF APPLICATION

Sikafloor® Marine-599 is designed as a part of the Sikafloor® Marine Deco systems as synthetic teak decking solution for external decks in shipbuilding, cruise and leisure boat construction.

This product is suitable for experienced professional users only.

Tests with actual substrates and conditions have to be performed ensuring workability, adhesion and material compatibility.

PRODUCT DATA SHEET Sikafloor® Marine-599

Version 03.01 (07 - 2024), en_US 012119015994001000

A) substrates must be 3 °C above the dew point

B) max. 80 % r.h. C) stored in sealed container in up-right position in a dry place between 5 and 30 °C, protected from direct sunlight

CURE MECHANISM

The curing of Sikafloor® Marine-599 takes place by a chemical reaction of the two components. Higher temperatures speed up and lower temperatures slow down the curing process.

CHEMICAL RESISTANCE

For advice contact the Technical Department of Sika Industry.

METHOD OF APPLICATION

Surface Preparation

Sikafloor® Marine-599 is installed on top of the deck levelling compound.

Metallic decks need to be prepared to SA 2.5 (ISO 8501). Aluminum decks must not be shot blasted. The prepared metallic surfaces need to be clean, free of dirt, grease, oil and loose particles before the SikaCor® ZP Primer is applied.

The application area must be protected against weather and direct sunlight.

Mixing process

Prior to mixing, stir part A. Add part B and mix continuously for 2 minutes until a homogeneous mix has been obtained.

Pour material into another container and mix again for at least 1 minute.

Use double mixing paddles not higher than 300 rpm to minimize air entrapment.

The curing time of Sikafloor® Marine-599 can be significantly shortened, by adding Sikafloor® Marine-001/-002 accelerators. The mixing procedure is the same as for the non-accelerated version, except that the accelerator is added 1 minute after start mixing A and B.

For further information regarding accelerators, check the API - Sikafloor® Marine-001/-002 or contact the Technical Department of Sika Industry.

For areas with cambers or slopes between 1 % and 3 % use Sikafloor® Marine Liquid PU Thickener. The dosage is between 1 % and 2 % in weight depending on the actual situation. For areas with higher cambers it may be required to add additional 1 % to 2 % of Sika® Extender T or Aerosil by weight to the mix. Alternatively, it is possible to reduce the layer thickness and apply multiple layers.

Note: By increasing the viscosity de-airing properties can be affected.

For liquid applied floors it is recommended to use Sikafloor® Marine-001/-002 to accelerate the curing and reduce the amount of flow.

Application

Sikafloor® Marine-599 is poured and spread evenly by means of a notched trowel, flat trowel or pin-rake. In critical areas a spike roller can be used to improve levelling and de-airing. For deeper sections (e.g. unevenness), it might be necessary to pre-level these sections. Ensure the pre-leveled sections have achieved "foot traffic" cure level prior to proceeding.

For liquid application on cambers and slopes multiple applications steps may be needed. Curing speed depends on temperature and layer thickness. Always consider the pot life to keep a wet edge.

Curing

Indications regarding curing details see table below.

Tempera- ture	Foot traffic	Light traffic ^A	Full cure
10 °C	30 hours	48 hours	6 days
20 °C	16 hours	24 hours	4 days
30 °C	12 hours	18 hours	3 days

A) food trolleys and light rolling equipment on soft wheels

Removal

Uncured Sikafloor® Marine-599 can be removed from tools and equipment with Sika® Colma Cleaner or another suitable solvent. Once cured, the material can only be removed mechanically.

Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

Application Limits

Freshly applied Sikafloor® Marine-599 must be protected from moisture, condensation and water for at least 1 day. Uncured material reacts in contact with water (foaming).

STORAGE CONDITIONS

Both components of Sikafloor® Marine-599 have to be kept between 5 °C and 30 °C in a dry place. Do not expose it to direct sunlight. After opening of the packaging, the contents need to be protected against moisture.

Minimum temperature during transportation is 5 °C

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

Safety Data Sheets

PACKAGING INFORMATION

Sikafloor® Marine-599 (A)

Pail	15 kg
Sikafloor® Marine-599 (B)	
Pail	5 kg

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by contacting SIKA's Technical Service Department via email at tsmh@us.sika.com. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product. SIKA warrants this product for one year from

date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. NO OTHER WARRANTIES EX-PRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FIT-**NESS FOR A PARTICULAR PURPOSE. SIKA SHALL** NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at https://usa.sika.com/en/group/SikaCorp/termsandconditions.html or by calling +1 800-933-7452.



Version 03.01 (07 - 2024), en_US 012119015994001000

Sika Corporation

30800 Stephenson Highway Madison Heights, MI 48071 U.S.A.

Telephone: +1 248-577-0020 Email: tsmh@us.sika.com www.sikausa.com

