

## PRODUCT DATA SHEET

# SikaTack® MOVE Transportation

All-in-one solution for Bus, Coach and Truck glass replacement

**TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)**

Chemical base	1-component polyurethane	
Color (CQP001-1)	Black	
Cure mechanism	Moisture-curing	
Density (uncured)	1.2 kg/l	
Non-sag properties (CQP061-1)	Very good	
Application temperature	product	5 – 35 °C
	ambient	5 – 35 °C
Skin time (CQP019-1)	20 minutes <sup>A</sup>	
Open time (CQP526-1)	15 minutes <sup>A</sup>	
Curing speed (CQP049-1)	See diagram 1	
Shore A hardness (CQP023-1 / ISO 48-4)	65	
Tensile strength (CQP036-1 / ISO 527)	8 MPa	
Elongation at break (CQP036-1 / ISO 37)	300 %	
Tear propagation resistance (CQP045-1 / ISO 34)	10 N/mm	
Tensile lap-shear strength (CQP046-1 / ISO 4587)	5 MPa	
Minimum Drive Away Time for supported glass	< 40 kg	2 hours <sup>B/C</sup>
	< 75 kg	4 hours <sup>B/C</sup>
Service Temperature CQP509-1 / CQP513-1)	-40 – 90 °C	
Shelf life (CQP016-1)	12 months <sup>D</sup>	

CQP = Corporate Quality Procedure  
<sup>C</sup>) 5 °C / 80 % r. h. – 40 °C / 20 % r. h.

<sup>A</sup>) 23 °C / 50 % r. h.  
<sup>D</sup>) storage below 25 °C

<sup>B</sup>) Details about MDAT contact Sika

**DESCRIPTION**

SikaTack® MOVE Transportation is a cold-applied adhesive specially designed for glass replacement and gap filling application for buses, coaches and trucks. It provides a good weathering stability and is therefore suitable for open joints.

**PRODUCT BENEFITS**

- Short Drive Away Time for commercial vehicles
- Suitable for bonding and gap filling
- Exhibits good weathering stability
- Compatible with Black-Primerless and All-Black installation process
- Solvent-free
- Ideal product for glass replacement on commercial vehicles

**AREAS OF APPLICATION**

SikaTack® MOVE Transportation has been specially designed as an all-in-one solution for the windshield replacement of commercial vehicles such as buses and trucks. Thanks to its weathering stability it can be used for both bonding and gap filling. It is ideal for mobile and in-house installations.

SikaTack® MOVE Transportation is suitable for experienced professional users only. This product and related process information is designed for vehicle Glass Replacement. For other applications, tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

**PRODUCT DATA SHEET**

SikaTack® MOVE Transportation  
 Version 04.02 (04 - 2022), en\_ZA  
 012002210093001000

## CURE MECHANISM

SikaTack® MOVE Transportation cures by reaction with atmospheric moisture. At low temperatures the water content of the air is generally lower and the curing reaction proceeds somewhat slower (see diagram 1).




Diagram 1: Curing speed of SikaTack® MOVE Transportation

## CHEMICAL RESISTANCE

SikaTack® MOVE Transportation is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

## METHOD OF APPLICATION

### Surface Preparation

Surfaces must be clean, dry and free from grease, oil, dust and contaminants.

The bond faces must be treated according Sika's Black-Primerless or All Black installation process. Further information on the application and use of Pre-treatments, can be found in the corresponding Product Data Sheet.

Glass without ceramic coatings need proper UV protection.

## Application

It is recommended to apply SikaTack® MOVE Transportation with a powerful battery operated application gun.

Consider that the viscosity will increase at low temperature. For easy application, condition the adhesive at ambient temperature prior to use.

To ensure a uniform thickness of the bondline it is recommended to apply the adhesive in form of a triangular bead (see figure 1).




Figure 1: Compressing adhesive bead to final size

The open time is significantly shorter in hot and humid climate. The glass must always be installed within the open time. Never install a glass after the product has built a skin.

## Removal

Uncured SikaTack® MOVE Transportation can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin have to be washed immediately using Sika® Cleaner-350H cleaning towels or a suitable industrial hand cleaner and water. Do not use solvents on skin!

## FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- Black-Primerless installation process chart
- All Black installation process chart

## PACKAGING INFORMATION

Unipack	600 ml
---------	--------

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

## DISCLAIMER

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

## PRODUCT DATA SHEET

SikaTack® MOVE Transportation  
Version 04.02 (04 - 2022), en\_ZA  
012002210093001000

## Sika South Africa (Pty) Ltd

9 Hocking Place,  
Westmead, 3608  
South Africa  
Phone +27 31 792 6500  
www.sika.co.za

