

**BUILDING TRUST** 

# PRODUCT DATA SHEET

# Sikasil® AS-785

Fast curing and structural assembly silicone adhesive

# TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Properties		Sikasil® AS-785 (A)	Sikasil® AS-785 (B)
Chemical base		2-component silicone	
Color (CQP001-1)		White	Black
	mixed	Black	
Cure mechanism		Polycondensation	
Cure type		Alkoxy	
Density (uncured)	mixed	1.38 kg/l	1.06 kg/l
		1.35 kg/l	
Mixing ratio	A:B by volume	10:1	
	A:B by weight	13:1	
Viscosity (CQP029-5 / ISO 3219)	at 0.89 s <sup>-1</sup>	1 200 Pa·s	400 Pa·s
Consistency		Paste	
Application temperature	ambient	5 – 40 °C	
Snap time (CQP554-1)		12 minutes <sup>A, B</sup>	
Tack free time (CQP019-3)		40 minutes <sup>A</sup>	
Shore A hardness (CQP023-1 / ISO 48-4)		45	
Tensile strength (CQP036-1 / ISO 527)		2 MPa	
100 % modulus (CQP036-1 / ISO 527)		1.2 MPa	
Elongation at break (CQP036-1 / ISO 527)		250 %	
Thermal resistance (CQP 513-1)	4 hours	190 °C	
	1 hour	200 °C	
Service temperature (CQP513-1)		-40 – 150 °C	
Shelf life		15 months <sup>C</sup>	9 months <sup>C</sup>
	A) ac ac (=c a)	1	

CQP = Corporate Quality Procedure

#### **DESCRIPTION**

Sikasil® AS-785 is a fast curing structural 2-component industrial silicone adhesive and sealant. It is none corrosive, has a very broad adhesion range as well as an outstanding long-term durability in harsh environment conditions.

## **PRODUCT BENEFITS**

- Outstanding adhesion and mechanical performance under harsh environment conditions
- Excellent adhesion to a wide variety of substrates
- Very good mechanical properties
- Performance retention over a wide temperature range
- Long-term durability
- Low volatility
- Meets EOTA ETAG 002
- UL® certified: UL94 V-1, QOQW2 (-40 °C 105 °C)

## AREAS OF APPLICATION

Sikasil® AS-785 is especially designed for fast and/or automated bonding of structural adhesive joints. Especially for interior or exterior applications where a high mechanical performance under harsh conditions are required, like in appliances, solar and automotive.

Common substrates are metals, particularly aluminum, glass, metal primers and paint coatings (2-part systems), ceramic materials and plastics.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

# PRODUCT DATA SHEET

**Sikasil® AS-785** Version 04.01 (04 - 2023), en\_DK 012703100850001000

<sup>&</sup>lt;sup>A)</sup> 23 °C / 50 % r. h.

B) The snap time can increase add. 6 min. with component B at the end of shelf life

C) storage below 25 °C

#### **CURE MECHANISM**

Sikasil® AS-785 starts to cure immediately after mixing the two components.

The speed of the reaction depends mainly on the temperature, i.e. the higher the temperature the faster the curing process. Heating above 50 °C could lead to bubble formation and is therefore not allowed.

The mixer open time, i. e. the time the material can remain in the mixer without flushing or extrusion of product, is significantly shorter than the snap time indicated above.

#### METHOD OF APPLICATION

#### Surface preparation

Surfaces must be clean, dry and free from grease, oil and dust. Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond.

#### **Application**

Before processing Sikasil® AS-785 both components have to be mixed homogeneously and air-bubble-free in the correct ratio as indicated with an accuracy of  $\pm$  10 %. Most commercially available metering and mixing equipment are suitable. For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

Consider that the B-component is moisturesensitive and must therefore only be exposed briefly to air.

Joints must be properly dimensioned.

#### Tooling and finishing

Tooling and finishing must be carried out within the snap time of the adhesive. No tooling agents must be used.

#### Removal

Uncured Sikasil® AS-785 can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

# **Application limits**

To exclude materials influencing Sikasil® AS-785, all materials such as gaskets, setting blocks, sealants etc., in direct and indirect contact have to be approved by Sika in advance.

Where two or more different reactive sealants are used, allow the first to cure completely before applying the next.

Sikasil® AS-785 may only be used for serial application after a detailed examination and written approval of the corresponding project details by Sika Industry.

#### **FURTHER INFORMATION**

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- General Guidelines
   Bonding and Sealing with Sikasil® AS-Products

# PACKAGING INFORMATION

Sikasil® AS-785 (A)

Pail	26 kg	
Drum	260 kg	
Sikasil® AS-785 (B)		
Pail	20 kg	
Sikasil® AS-785 (A+B)		
Side by side cartridge	490 ml	

#### **BASIS OF PRODUCT DATA**

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

#### **HEALTH AND SAFETY INFORMATION**

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

#### **DISCLAIMER**

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or endusers of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buver or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted. and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.



Version 04.01 (04 - 2023), en\_DK 012703100850001000 Sika Danmark A/S Hirsemarken 5 3520 Farum Tlf. +45 48 18 85 85 www.sika.dk







