

PRODUCT DATA SHEET

Sikaflex®-953 AF

Fast-curing, fungus resistant 2-component STP assembly adhesive and sealant

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Properties	Sikaflex®-953 AF (A)	Sikaflex®-905 (B)
Chemical base	Silane terminated polymer (STP)	
Colour (CQP001-1)	Grey	White
	mixed	
	Grey	
Density (uncured)	1.40 kg/l	1.17 kg/l
	mixed (calculated)	
	1.38 kg/l	
Mixing ratio	A:B by volume	
	A:B by weight	
	10:1	
	11.7:1	
Non-sag properties (CQP061-1)	Fair	
Application temperature	5 – 40 °C	
Skin time (CQP019-1)	35 minutes ^A	
Snap time (CQP554-1)	20 minutes ^A	
Curing speed (CQP046-1)	(see table) ^A	
Shrinkage (CQP014-1)	2 %	
Shore A hardness (CQP023-1 / ISO 48-4)	40	
Tensile strength (CQP036-1 / ISO 527)	2.5 MPa	
Elongation at break (CQP036-1 / ISO 527)	350 %	
Tear propagation resistance (CQP045-1 / ISO 34)	6 N/mm	
Tensile lap-shear strength (CQP046-1 / ISO 4587)	1.4 MPa	
Thermal resistance (CQP 513-1)	1 hour	160 °C
Service temperature (CQP513-1)	-45 – 90 °C	
Shelf life	9 months ^B	
Mixer	Statomix® MS 13-18 G	

CQP = Corporate Quality Procedure

^A) 23 °C / 50 % r. h.^B) storage between 5 and 25 °C, B-component is frost sensitive
DESCRIPTION

Sikaflex®-953 AF is a 2-component Silane Terminated Polymer (STP) assembly adhesive which cures by chemical reaction of the two components. It largely prevents fungal and bacterial growth and meets hygiene requirements for ventilation and air-conditioning. Owing to its good weathering resistance and gap-filling performance it can also be used for exterior sealing joints. It is also very suitable where pumping over a long distance is required.

PRODUCT BENEFITS

- Resistant to fungal and bacterial growth according DIN EN ISO 846: 1997-10
- Meets hygiene requirements for ventilation and air-conditioning systems and units according VDI 6022 Blatt 1:2011-07
- Great weathering and ageing resistance
- Adheres well to most common substrates with a minimal pre-treatment
- Solvent- and isocyanate-free
- Good gap-filling capabilities
- Pumpable over long distances

AREAS OF APPLICATION

Sikaflex®-953 AF is designed for sealing and bonding of heat, ventilation and air conditioning units, where the attainment of early strength is required.

Possible substrate materials are metals, particularly aluminium (including anodised), steel (including phosphated, chromated, galvanized), metal primers and paint coatings (2-part systems), ceramic materials and plastics. Seek manufacturer's advice and perform tests on original substrates before using Sikaflex®-953 AF on materials prone to stress cracking. This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

PRODUCT DATA SHEET

Sikaflex®-953 AF

Version 03.01 (10 - 2023), en_GB
012301219530001150

CURE MECHANISM

The curing of Sikaflex®-953 AF takes place by chemical reaction of the two components.

Time [h]	Strength [MPa]
2	0.4
4	0.8
6	1.0

Table 1: Lap shear strength (CQP 046-1) at 23 °C / 50 % r. h.

CHEMICAL RESISTANCE

Sikaflex®-953 AF is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

METHOD OF APPLICATION

Surface Preparation

Surfaces must be clean, dry and free from grease, oil and dust. Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond. All pre-treatment steps must be confirmed by preliminary tests on original substrates considering specific conditions in the assembly process.

Application

Sikaflex®-953 AF need to be processed with an adequate dispensing system. The mixer type needs to be respected (see table Typical Product Data).

Sikaflex®-953 AF can be applied between 5 °C and 40 °C but changes in reactivity and application properties have to be considered.

The optimum temperature for substrate and sealant is between 15 °C and 25 °C. To ensure a uniform thickness of the bondline it is recommended to apply the adhesive in form of a triangular bead (see figure 1).




Figure 1: Recommended bead configuration

The open time is significantly shorter in hot and humid climate. The parts must always be joint within the open time. As a rule of thumb, a change of + 10 °C reduces the open time by half.

Sikaflex®-953 AF is processed with pump equipment. For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

Tooling and finishing

Tooling and finishing must be carried out within the open time of the adhesive. We recommend the use of Sika® Tooling Agent N. Other finishing agents must be tested for suitability and compatibility.

Removal

Uncured Sikaflex®-953 AF can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically.

Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

Overpainting

Sikaflex®-953 AF can be best painted within the skin formation time. If painting process takes place after the sealant has built a skin, adhesion could be improved by treating the joint surface with Sika® Aktivator-100 or Sika® Aktivator-205 prior to paint process. If the paint requires a baking process (> 80 °C), best performance is achieved by allowing the sealant to fully cure first. All paints have to be tested by carrying preliminary trials under manufacturing conditions. The elasticity of paints is usually lower than that of sealants. This could lead to cracking of the paint in the joint area.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- Sika Pre-treatment Chart
- Silane Terminated Polymer

PACKAGING INFORMATION

Sikaflex®-953 AF

Drum	195 l
------	-------

Sikaflex®-905 (B)

Pail	23 l
------	------

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

DISCLAIMER

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PRODUCT DATA SHEET

Sikaflex®-953 AF
Version 03.01 (10 - 2023), en_GB
012301219530001150

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited

