

BUILDING TRUST

PRODUCT DATA SHEET Sikafloor[®] Marine KG-404 N

Medium weight primary deck covering mortar for interior decks

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical Base			Polymer modified cement mortar
Color			Grey
Cure Mechanism			Hydraulic
Density	mixed		1.4 kg/l
		cured	1.3 kg/l
Mixing Ratio		per 20 kg bag	4.6 – 5.4 liters
Substrate Temperature			5 – 30 °C
Application Thickness			5 – 100 mm
Coverage	per 20 kg bag	at layer thickness 1 mm	15 m ²
Working Time (CQP599-9)			20 minutes ^A
Ready to Walk on (CQP600-3)	depending on h	numidity and ventilation	16 hours ^A
Compressive Strength (CQP599-2)			20 MPa ^B
Flexural Strength (CQP599-1)			4 MPa ^B
Modulus of Elasticity in Compression (CQP599-6 / EN 13412)			7.4 GPa ^B
Linear Shrinkage (CQP599-5)			0.02 % ^B
Shelf Life			12 months ^c
CQP = Corporate Quality Procedure A) 2	3 °C / 50 % r. h.	^{B)} after 28 days	^{C)} stored in a dry, cool place below 25 °C

DESCRIPTION Sikafloor® Marine KG-404 N is a 1-component

flame resistance.

ives.

medium weight leveling mortar based on

polymer modified cement with excellent

Sikafloor® Marine KG-404 N is tested accord-

ing to FTP Code system and approved ac-

cording to the IMO Marine Equipment Direct-

PRODUCT BENEFITS

- Non combustible
- Low E-modulus
- One component, ready to mix
- Easy applicable
- Suitable for sloped surfaces
- Can be pumped

^{C)} stored in a dry, cool place below 25 °C

AREAS OF APPLICATION

Sikafloor® Marine KG-404 N is applied on interior decks, to level the surface prior to the application of deck finishing materials such as: carpets, tiles, parquet, rubber and vinyl. It is suitable for application in wet and dry accommodation areas. For wet areas prior to tiles application, the substrate has to be additionally treated with a water resistant membrane (e.g. Sikafloor® Marine Elastic). This product is suitable for experienced professional users only. Test with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

PRODUCT DATA SHEET Sikafloor® Marine KG-404 N Version 03.01 (03 - 2023), en_MY 019319000114001000

CURE MECHANISM

Sikafloor[®] Marine KG-404 N cures by way of hydraulic curing.

METHOD OF APPLICATION

Surface Preparation

For leveling applications, the surface has to be clean, free from dust, grease, oils and other substances, which may impair adhesion. Rust has to be removed with a steel brush or other appropriate means, followed by vacuum cleaning.

The surface has to be primed with Sikafloor[®] Marine Primer C using a long hair roller. After drying of the Sikafloor[®] Marine Primer C, Sikafloor[®] Marine KG-404 N may be applied.

For wet areas the surface has to be treated with a water resistant membrane (e.g. Sika-floor® Marine Elastic).

Before application of vinyl and carpet coverings, ensure that a thin self levelling mortar such as Sikafloor[®] Marine 100 is applied to obtain an even floor.

Sikafloor[®] Marine KG-404 N applications on aluminum or zinc rich shop primer coated decks, require a tie coat of SikaCor[®] ZP Primer or another suitable tie coat prior the priming step with Sikafloor[®] Marine Primer C.

Mixing Process

One bag of Sikafloor[®] Marine KG-404 N is mixed with 4.6 to 5.4 liters cold potable water. The mixing time with a drilling machine and proper mixing paddles is approx. 5 minutes (not higher than 400 rpm).

Ensure the powder is mixed completely (bottom and side walls of the bucket).

For larger amounts, it may be mixed with a cement mixer. In any case, ensure a homogenous mortar is obtained before application.

Application

Apply the mortar with a steel board or a straight edge.

Sikafloor[®] Marine KG-404 N has to be applied within 30 minutes after mixing. At temperatures above 30 °C the open time will be reduced to 10 minutes or less.

For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

Curing

After application, the finished areas have to be protected against direct heat (e.g. cutting or welding from beneath), sunlight and draught during the curing process for at least 12 hours.

Before Sikafloor[®] Marine KG-404 N is covered with dense materials such as vinyl, epoxy or polyurethane coatings, etc., ensure that the remaining moisture level is below 4 %. If covered by an epoxy or polyurthane material, a smoothening layer of Sikafloor[®] Marine-118 FC or -190 may be needed.

Test procedure to determine the dryness (according ASTM D 4263): put a PE-plastic foil 1 m x 1 m on the surface of the applied mortar floor, tape the perimeter and leave for one day. The curing is complete if there is no water condensation on the foil or a visible color difference between covered and uncovered surface.

Removal

Excess material can best be removed before curing with a trowel wipe or water.

Fresh Sikafloor[®] Marine KG-404 N may be removed from tools and equipment with water. Once cured, the material can only be removed mechanically.

Exposed hands and skin shall be washed immediately with water. Use a suitable skin protection hand cream.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

20 kg

- Safety Data Sheet
- Application Manual

Bag

Sikafloor[®] Marine KG-404 N

PACKAGING INFORMATION

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PRODUCT DATA SHEET Sikafloor® Marine KG-404 N Version 03.01 (03 - 2023), en_MY 019319000114001000 Sika Kimia Sdn. Bhd. Lot 689, Nilai Industrial Estate, 71800 Nilai, Negeri Sembilan D.K. Malaysia Phone: +606-7991762 e-mail: info@my.sika.com Website: www.sika.com.my



